

Technical Data Sheet

Petrothene LR590005

W&C Polyolefin Compound



Product Description

Petrothene LR590005 is a high density resin selected by customers for use as primary insulation for electronic cables. This resin exhibits low shrinkback after extrusion, contains a lower level of antioxidant than LR590001, and is not suitable for the telecommunications applications for which LR590001 was formulated. Antioxidant has been added to LR590005 along with a metal deactivator to ensure thermal stability during processing and to prevent degradation from copper while the cable is in service.

Petrothene LR590005 meets the requirements of the following: ASTM D 1248-2, Type III, Class A, Category 4, Grades E8 and E9; Federal LP390C, Type II, Class H, Category 4, Grade 1; REA PE-22; REA 7CFR 1755.390.

Regulatory Status

For regulatory compliance information, see *Petrothene* LR590005 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Wire & Cable
Market	Wire & Cable
Processing Method	Wire & Cable

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	0.80	g/10 min	0.80	g/10 min	ASTM D1238
Density, (23 °C)	0.948	g/cm ³	0.948	g/cm ³	ASTM D1505
Mechanical					
Tensile Stress at Break	2350	psi	16.2	MPa	ASTM D638
Tensile Stress at Yield	3150	psi	21.7	MPa	ASTM D638
Tensile Elongation at Break	800	%	800	%	ASTM D638
Thermal Stress Crack Resistance, F ₅₀ in water at 100 °C	0 Failures at 14 days		0 Failures at 14 days		ASTM D2951
Environmental Stress Crack Resistance, F ₂₀ (100% Igepal®, Cond B)	0 Failures at 7 days		0 Failures at 7 days		ASTM D1693
Hardness					
Shore Hardness, (Shore D)	65		65		ASTM D2240
Thermal					
Vicat Softening Temperature	257	°F	125	°C	ASTM D1525
Low Temperature Brittleness, F ₅₀	<-105	°F	<-76	°C	ASTM D746
Electrical					
Volume Resistivity	1 x 10 ¹⁸	ohm*cm	1 x 10 ¹⁸	ohm*cm	ASTM D257
Dielectric Constant, 1 MHz	2.33		2.33		ASTM D150

LyondellBasell
Technical Data Sheet
Date: 7/25/2017

Page 1 of 4

Petrothene LR590005
Recipient Tracking #:
Request #: 907645

Dissipation Factor, 1 MHz	0.00004	0.00004	ASTM D150
---------------------------	---------	---------	-----------

Notes

Igepal® is a registered trademark of Rhodia.

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Petrothene LR590005, like other thermoplastic polyolefin resins, can be extruded using a conventional extruder. Below are suggested extrusion conditions for *Petrothene* LR590005. These conditions are intended as general guidelines only, and are not optimum values, since manufacturing variables such as extruder type and size have an effect on processing of thermoplastic resins.

<u>Extruder Zone</u>	<u>Temperature Range</u>	<u>Extruder Zone</u>	<u>Temperature Range</u>
Feed	300 - 325 °F (149 - 163 °C)	Adapter	475 - 500 °F (246 - 260 °C)
Zone 2	350 - 400 °F (177 - 204 °C)	Die	475 - 500 °F (246 - 260 °C)
Zone 3	400 - 450 °F (204 - 232 °C)	Melt Temperature	475 - 500 °F (246 - 260 °C)
Zone 4-X	460 - 500 °F (238 - 260 °C)		

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2017

Disclaimer

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally.

SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

Users should review the applicable Safety Data Sheet before handling the product.

This product(s) may not be used in the manufacture of any of the following, without prior written approval by Seller for each specific product and application:

- (i) U.S. FDA Class I or II Medical Devices; Health Canada Class I, II or III Medical Devices; European Union Class I or II Medical Devices;
- (ii) film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned medical devices;
- (iii) packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration;
- (iv) tobacco related products and applications, electronic cigarettes and similar devices.
- (v) safety components in automotive applications, for example: air bags, air bag unit housings and covers, seat belt mechanisms, brake systems, pedals and pedal supports, steering systems.

The product(s) may not be used in:

- (i) U.S. FDA Class III Medical Devices; Health Canada Class IV Medical Devices; European Class III Medical Devices;
- (ii) applications involving permanent implantation into the body;
- (iii) life-sustaining medical applications.

All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

In addition to the above, LyondellBasell may further prohibit or restrict the use of its products in certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the power to win, Glacido, Hifax, Hiflex, Histif, Hostacom, Hostalen, Hyperzone, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-fax, Punctilious, Purell, Refax, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec are trademarks owned and/or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Metocene, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo and Ultrathene are registered in the U.S. Patent and Trademark Office.

