

Preliminary Data Sheet

Petrothene

LR763011

High Density Polyethylene

Blow Molding Grade

Melt Index: 0.35 Density: 0.951



Applications

Petrothene LR763011 exhibits an enhanced balance of stiffness and environmental stress crack resistance. Typical applications include bottles for bleach, detergents, and household chemicals. This resin contains synthetic antistat.

Regulatory Status

LR763011 meets the requirements of the Food and Drug Administration regulation 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food..." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information about the use of specific products for specific application.

Processing Techniques

Specific recommendations for processing LR763011 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	0.35	g/10 min	D 1238
Density	0.951	g/cc	D 1505
Tensile Strength @ Yield	3,900	psi	D 638
Elongation @ Break	>500	%	D 638
Flexural Modulus (1% Secant)	169,800	psi	D 790
Tensile Impact	158	ft-lb/in.	D 1822
Low Temperature Brittleness, F ₅₀	<-76	°C	D 746
Vicat Softening Point	126	°C	D 1525
Environmental Stress Crack Resistance, F ₅₀	55	hrs	D 1693 ¹

¹ 100% Igepal® CO-630, 50°C

® Igepal is a registered trademark of Rhône-Poulenc Co., Inc.

LyondellBasell markets this product through the following entities:

Equistar Chemicals, LP
 Basell Sales & Marketing Company B.V.
 Basell Asia Pacific Limited
 Basell International Trading FZE
 LyondellBasell Australia Pty Ltd

Petrothene is a trademark owned or used by LyondellBasell group companies. *Petrothene* is registered in the U.S. Patent and Trademark Office.

Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product(s) may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application.

Users should review the applicable Material Safety Data Sheet before handling the product.

Equistar Chemicals, LP
 1221 McKinney, Suite 700
 P. O. Box 2583
 Houston, Texas 77252-2583
 (800) 615-8999
www.lyondellbasell.com

© LyondellBasell Industries Holdings, B.V. 2012

3011/0909