


Petrothene®

M2520

Low Density Polyethylene
Film Grade
Melt Index 2.0 Density 0.925
Applications

PETROTHENE M2520 is a film grade resin that exhibits excellent optics, good gloss, good bubble stability and outstanding processability. A typical application for this resin is high clarity packaging that requires higher modulus.

Regulatory Status

M2520 meets the requirements of the Food and Drug Administration, regulation 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles that contact food except for articles used for packing or holding food during cooking." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information.

Processing Techniques

Specific recommendations for processing M2520 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	2.0	g/10 min	D 1238
Base Resin Density	0.925	g/cc	D 1558
Film*			
Haze	5.5	%	D 1003
Gloss, 45°	70	units	D 2457
Dart Drop Impact Strength, F ₅₀	75	g	D 1709
Tensile Strength @ Break, MD (TD)	4,300 (3,300)	psi	D 882
Tensile Strength @ Yield, MD (TD)	1,700 (1,900)	psi	D 882
Elongation @ Break, MD (TD)	130 (470)	%	D 882
1% Secant Modulus, MD (TD)	39,000 (49,000)	psi	E 111
Elmendorf Tear, MD (TD)	270 (80)	g	D 1922

Product M2520FNx02

Slip, ppm 800
 Antiblock, ppm 1,000

These are typical values and are not to be construed as specific product limits.

* Data obtained from film produced with a 375°F (191°C) melt extrusion temperature 2:1 BUR, 1.0 mil (32 micron) gauge, 0.025" die gap at 50 lb/hr on a 4" die. Optical properties are for additive free product.

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

®Equistar and Petrothene are registered trademarks of Equistar Chemicals, LP.



Lyondell Chemical Company
 1221 McKinney, Suite 700
 P.O. Box 2583
 Houston, Texas 77252-2583
 800.615.8999
<http://www.Lyondell.com>