

Petrothene

NA940

Low Density Polyethylene

Film Extrusion Grade

Melt Index: 0.25 Density: 0.918

lyondellbasell

Applications

Petrothene NA940 is a series of resins used for heavy duty film applications. Excellent puncture resistance combined with impact properties make NA940 an exceptional choice when selected by customers for bags used to package fertilizer, peat moss, decorative stone and agricultural and construction materials. NA940 also has excellent heat shrink properties.

Regulatory Status

The base resin NA940 meets the requirements of the Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer "... in articles or components of articles intended for use in contact with food..." Specific limitations or conditions of use may apply. Contact your Equistar product safety representative for more information.

Processing Techniques

NA 940 has excellent processability, bubble stability and good heat sealing over a wide range of extrusion conditions; however, recommended conditions are melt temperatures between 330°- 430°F (165°- 221°C) and blow-up ratios between 1.8:1 and 2.5:1. Drawdown to 1.5 mil (38.1 microns) is possible at commercial rates when proper extrusion techniques are used. Specific recommendations for processing NA 940 can be made only when the end use applications, required properties and processing equipment are known.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	0.25	g/10 min	D1238
Base Resin Density	0.918	g/cc	D1505
Vicat Softening Point	90	°C	D1525
Film*			
Dart Drop Impact Strength, F ₅₀	220	g	D1709
Tensile Strength, MD (TD)	3,000 (2,800)	psi	D882
Elongation, MD (TD)	300 (500)	%	D882
1 % Secant Modulus, MD (TD)	24,000 (27,000)	psi	E111
Elmendorf Tear Strength, MD (TD)	220 (200)	g	D1922
Molding			
Low Temperature Brittleness, F ₅₀	<-76	°C	D746
Tensile Strength @ Break	2,100	psi	D638
Elongation @ Break	>600	%	D638
Flexural Modulus	34,000	psi	D790
Hardness, Shore D	50		D2240
Environmental Stress Crack Resistance, # Failures in 100% Igepal®	0 in 7 days		D1693
Products			
	NA940000	NA940085	NA940094
Slip (ppm)	None	None	500
Antiblock (ppm)	None	4,000	4,000

* Data obtained from film produced on a 3½" (89 mm) blown film line, commercially available 8" (203 mm) die, 430°F (221°C) melt extrusion temperature, 2:1 BUR, 2.0 mil (51 micron) gauge, 0.025" die gap at 170 lb/hr.

Igepal® is a registered trademark of the Rhone-Poulenc Co., Inc.

These are typical values not to be construed as specification limits.

See Page 2 for Additional Information

*Petrothene***NA940**

Low Density Polyethylene

Film Extrusion Grade

Melt Index: 0.25 Density: 0.918

lyondellbasell

LyondellBasell markets this product through the following entities:

Equistar Chemicals, LP
Basell Sales & Marketing Company B.V.
Basell Asia Pacific Limited
Basell International Trading FZE
LyondellBasell Australia Pty Ltd

Petrothene is a trademark owned or used by the LyondellBasell family of companies. *Petrothene* is registered in the U.S. Patent and Trademark Office.

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

This product(s) may not be used in:

(i) any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I Medical Devices, without prior notification to Seller for each specific product and application; or

(ii) the manufacture of any of the following, without prior written approval by Seller for each specific product and application: (1) U.S. FDA Class II, Health Canada Class II or Class III, and/or European Union Class II Medical Devices; (2) film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned Medical Devices; (3) packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; (4) tobacco related products and applications; (5) electronic cigarettes and similar devices; and (6) pressure pipe or fittings that are considered a part or component of a nuclear reactor.

(iii) Additionally, the product(s) may not be used in: (1) U.S. FDA Class III, Health Canada Class IV, and/or European Class III Medical Devices; (2) applications involving permanent implantation into the body; (3) life-sustaining medical applications; and (4) lead, asbestos or MTBE related applications.

All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

Users should review the applicable Material Safety Data Sheet before handling the product.

Equistar Chemicals, LP
1221 McKinney Street, Suite 300
Houston, Texas 77010
(888) 777-0232
www.lyondellbasell.com

© LyondellBasell Industries Holdings, B.V. 2014

6723-15/0714

Page 2 of 2