



Home / Products & Technology / Polymers / **Petrothene NA960080**

# Petrothene NA960080

## Description

*Petrothene* NA960080 is a natural low density polyethylene resin formulated for use as primary insulation for coaxial and control cable applications.

## Availability

North America

[» CustomerXpress](#)[» Find a Sales Contact](#)[» Request Product Information](#)

### Legend

SDS - Safety Data Sheet

PSB - Product Stewardship Bulletin

[Information](#)[SDS](#)[Technical Literature](#)

## Product Data and Technical Information

### Typical Properties

|                                |                               |
|--------------------------------|-------------------------------|
| Melt Flow Rate (190°C/2.16 kg) | <b>1.0 g/10 min</b>           |
| Base Resin Density (23°C)      | <b>0.919 g/cm<sup>3</sup></b> |

## Process

Wire & Cable

## Resin

Low Density Polyethylene

## Applications

Wire & Cable

This site uses cookies. By continuing to browse the site, you agree to our use of cookies.

[» ACCEPT](#)[Privacy](#)