

Petrothene

NA960

Low Density Polyethylene

Film Extrusion Grade

Melt Index: 1.0 Density: 0.920



Applications

Petrothene NA960 is a series of resins selected by customers for use in a wide variety of industrial film applications where high impact strength and excellent drawdown are needed. NA960 exhibits good uniformity, ease of processing and good tensile strength.

Regulatory Status

The base resin NA960 meets the requirements of the Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer "... in articles or components of articles intended for use in contact with food..." Specific limitations or conditions of use may apply. Contact your Equistar product safety representative for more information.

Processing Techniques

Specific recommendations for processing NA960 can be made only when the end use applications, required properties and processing equipment are known.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	1.0	g/10 min	D1238
Base Resin Density	0.920	g/cc	D1505
Vicat Softening Point	92	°C	D1525
Film*			
Dart Drop Impact Strength, F ₅₀	120	g	D1709
Tensile Strength, MD (TD)	3,500 (2,400)	psi	D882
Elongation, MD (TD)	200 (500)	%	D882
Secant Modulus, MD (TD)	29,000 (34,000)	psi	E111
Elmendorf Tear Strength, MD (TD)	300 (130)	g	D1922
Molding¹			
Tensile Strength	2,100	psi	D638
Elongation @ Break	660	%	D638
Products			
	NA960000	NA960070	NA960083
Slip (ppm)	None	500	None
Antiblock (ppm)	None	1,000	4,000

* Data obtained from film produced on a 3½" (89 mm) blown film line, commercially available 8" (203 mm) die, 350°F (177°C) melt extrusion temperature, 2:1 BUR, 1.25 mil (32 micron) gauge, 0.025" die gap at 150 lb/hr.

¹ Data derived from type IV specimen, 75 mil plaque @ 20" min.

These are typical values not to be construed as specification limits.

See Page 2 for Additional Information

*Petrothene***NA960**

Low Density Polyethylene

Film Extrusion Grade

Melt Index: 1.0 Density: 0.920

lyondellbasell

LyondellBasell markets this product through the following entities:

Equistar Chemicals, LP
Basell Sales & Marketing Company B.V.
Basell Asia Pacific Limited
Basell International Trading FZE
LyondellBasell Australia Pty Ltd

Petrothene is a trademark owned or used by the LyondellBasell family of companies. *Petrothene* is registered in the U.S. Patent and Trademark Office.

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.

This product(s) may not be used in:

(i) any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I medical devices, without prior notification to Seller for each specific product and application; or
(ii) the manufacture of any of the following, without prior written approval by Seller for each specific product and application: U.S. FDA Class II Medical Devices; Health Canada Class II or Class III Medical Devices; European Union Class II Medical Devices; film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned medical devices; packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; and tobacco related products and applications. Additionally, the product(s) may not be used in: (i) U.S. FDA Class III Medical Devices; Health Canada Class IV Medical Devices; European Class III Medical Devices; (ii) applications involving permanent implantation into the body; (iii) life-sustaining medical applications; and (iv) lead, asbestos or MTBE related applications. All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

Users should review the applicable Material Safety Data Sheet before handling the product.

Equistar Chemicals, LP
1221 McKinney, Suite 700
P. O. Box 2583
Houston, Texas 77252-2583
(888) 777-0232
www.lyondellbasell.com

© LyondellBasell Industries Holdings, B.V. 2013

6723-20/1013

Page 2 of 2