


Plexar®

PX3080

Extrudable Tie Layer Resin
Anhydride Modified LLDPE
Melt Index 1.8 Density 0.910
Pellet
General Description

Plexar® tie-layers are chemically modified resins used to bond unlike materials, primarily in packaging and industrial applications. Common adherents include polyethylene resins and copolymers, such as EVA or EMA, polypropylene, polyamide (nylon), ethylene vinyl alcohol copolymers (EVOH), ionomer and other sealants, polyethylene terephthalate (PET) resins and copolymers, styrenic polymers, metal, paper and many others. Product grades tailored for blown and cast films, sheet and thermoforming, blow molding, extrusion coating and lamination, tubing, pipe, spray coating and other specialty applications are available in pellet form. Contact your Plexar sales and/or Equistar technical service representative for more information and specific recommendations for your application(s).

Regulatory Status

PX3080 meets the requirements for the Food and Drug Administration regulation 21CFR 175.105 for adhesives. This regulation describes adhesives which may be safely used as components of articles intended for use in packaging, transporting or holding food in accordance with conditions outlined in that regulation. For an adhesive formulation to be used in compliance with Section 175.105, it must be used under conditions that prevent the material from becoming a component of food in more than insignificant, *de minimis*, amounts. For more information, please contact your Lyondell product safety representative.

Processing Techniques

A process melt temperature above 410°F (210°C) is recommended to ensure adhesion between adherents. More specific suggestions can be made only when equipment, process parameters and conditions of use are known. Contact your Equistar Plexar technical service representative for more information.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	1.8	g/10 min	D 1238
Density	0.910	g/cc	D 1505
Vicat Softening Point	98.0	°C	D 1525
Blown Film			
	2.0 mil gauge; 2:1 BUR		
Notched Elmendorf Tear, MD (TD)	840 (1,030)	g	D 1922
Tensile Strength @ Yield, MD (TD)	8.8 (9.7)	Mpa	D 882
Tensile Strength @ Break, MD (TD)	22.8 (22.2)	Mpa	D 882
Elongation @ Yield, MD (TD)	16 (7)	%	D 882
Elongation @ Break, MD (TD)	790 (800)	%	D 882
WVTR	8.9	g/m ² /day	F372*

* @ 100% Humidity

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

*Plexar is a registered trademark of Equistar Chemicals, LP.



Lyondell Chemical Company
 1221 McKinney, Suite 700
 P.O. Box 2583
 Houston, Texas 77252-2583
 800.615.8999
<http://www.Lyondell.com>