

Plexar

PX9125

Extrudable Tie Layer Resin

Anhydride Modified LDPE

Melt Index 6.1 Density 0.922

lyondellbasell

General Description

Plexar tie-layers are chemically modified resins used to bond unlike materials, primarily in packaging and industrial applications. Common adherents include polyethylene resins and copolymers, such as EVA or EMA, polypropylene, polyamide (nylon), ethylene vinyl alcohol copolymers (EVOH), ionomer and other sealants, polyethylene terephthalate (PET) resins and copolymers, styrenic polymers, metal, paper and many others. Product grades tailored for blown and cast films, sheet and thermoforming, blow molding, extrusion coating and lamination, tubing, pipe, spray coating and other specialty applications are available in pellet form. Contact your Plexar sales and/or Equistar technical service representative for more information and specific recommendations for your application(s).

Regulatory Status

PX9125 meets the requirements for the Food and Drug Administration regulation 21CFR 175.105 for adhesives. This regulation describes adhesives which may be safely used as components of articles intended for use in packaging, transporting or holding food in accordance with conditions outlined in that regulation. For an adhesive formulation to be used in compliance with Section 175.105, it must be used under conditions that prevent the material from becoming a component of food in more than insignificant, *de minimis*, amounts. For more information, please contact your Lyondell product safety representative.

Processing Techniques

A process melt temperature above 410°F (210°C) is recommended to ensure adhesion between adherents. More specific suggestions can be made only when equipment, process parameters and conditions of use are known. Contact your Equistar Plexar technical service representative for more information.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	6.1	g/10 min	D 1238
Density	0.922	g/cc	D 1505
Vicat Softening Point	92.0	°C	D 3895

LyondellBasell markets this product through the following entities:

Equistar Chemicals, LP
 Basell Sales & Marketing Company B.V.
 Basell Asia Pacific Limited
 Basell International Trading FZE
 LyondellBasell Australia Pty Ltd

Plexar is a trademark owned or used by one of the LyondellBasell family of companies. Trademark Plexar is registered in the U.S. Patent and Trademark Office.

Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product(s) may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application.

Users should review the applicable Material Safety Data Sheet before handling the product.

Equistar Chemicals, LP
 1221 McKinney, Suite 700
 P. O. Box 2583
 Houston, Texas 77252-2583
 (800) 615-8999
www.lyondellbasell.com

© LyondellBasell Industries Holdings, B.V. 2011

3458/0711