

Technical Data Sheet**Premi-glas 1203-30**

Thermoset, Unspecified
LyondellBasell Industries
Engineering Plastics

Product Description

Premi-Glas® 1203-30 is a versatile fiberglass reinforced thermoset sheet molding compound for automotive body panel, personal watercraft or structural and semi-structural applications where excellent surface appearance, high strength, and durability are required.

Key Features and Benefits:

- Excellent surface profile for highly visible painted surfaces.
- Low moisture absorption and long term durability.
- Accepts automotive primers and powder in-mold-coatings.
- Excellent flexural strength and outstanding toughness.
- Standard colors are unpigmented or grey. Limited pigmentability.

General

Material Status	• Commercial: Active		
Availability	• North America		
Filler / Reinforcement	• Glass Fiber		
Features	• Durable • Good Surface Finish	• Good Toughness • High Strength	• Low Moisture Absorption • Paintable
Uses	• Automotive Applications	• Marine Applications	• Structural Parts
Appearance	• Natural Color		
Forms	• SMC - Sheet Molding Compound		


Physical	Nominal Value (English)	Nominal Value (SI)	
Density / Specific Gravity	1.95	1.95 g/cm ³	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus (Compression Molded)	2.20E+6 psi	15200 MPa	ASTM D638
Tensile Strength (Compression Molded)	14500 psi	100 MPa	ASTM D638
Tensile Elongation			ASTM D638
Break, Compression Molded	1.2 %	1.2 %	
Flexural Modulus (Compression Molded)	1.50E+6 psi	10300 MPa	ASTM D790
Flexural Strength (Compression Molded)	30500 psi	210 MPa	ASTM D790
Poisson's Ratio	0.30	0.30	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (Compression Molded)	18 ft·lb/in	960 J/m	ASTM D256
Unnotched Izod Impact (Compression Molded)	28 ft·lb/in	1500 J/m	ASTM D4812
Thermal	Nominal Value (English)	Nominal Value (SI)	
CLTE			
Flow ¹	1.4E-5 in/in/°F	2.5E-5 cm/cm/°C	
Transverse ²	1.9E-5 in/in/°F	3.5E-5 cm/cm/°C	
Thermal Conductivity	2.1 Btu·in/hr/ft ² /°F	0.30 W/m/K	

Technical Data Sheet



Premi-glas 1203-30

Thermoset, Unspecified
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Mold Temperature	300 °F	149 °C
Injection Pressure	500 to 1000 psi	3.45 to 6.89 MPa

Technical Data Sheet

**Premi-glas 1203-30**

Thermoset, Unspecified
LyondellBasell Industries
Engineering Plastics

Notes

¹ XY Direction

² Z Direction

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.