

## Technical Data Sheet



# Premi-glas 3100-22

Thermoset, Unspecified  
LyondellBasell Industries  
Engineering Plastics

### Product Description

Premi-Glas® 3100-22 is a fiberglass reinforced thermoset bulk molding compound for electrical and flame retardant applications.

- Good dimensional stability, including excellent thermal resistance.
- Pigmentable for molded-in color; best appearance with mold texture.
- Excellent property retention in cold and hot environments.
- Recognized by Underwriters Laboratories, File # E42524.
- Underwriters Laboratories 94-VO flame resistance at 1.5mm thickness.

### General

|                        |                                                                                                                                                                          |
|------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Material Status        | • Commercial: Active                                                                                                                                                     |
| Availability           | • North America                                                                                                                                                          |
| Filler / Reinforcement | • Glass Fiber                                                                                                                                                            |
| Additive               | • Flame Retardant                                                                                                                                                        |
| Features               | <ul style="list-style-type: none"> <li>• Flame Retardant</li> <li>• Good Colorability</li> <li>• Good Dimensional Stability</li> <li>• Medium Heat Resistance</li> </ul> |
| Uses                   | • Electrical/Electronic Applications                                                                                                                                     |
| UL File Number         | • E42524                                                                                                                                                                 |
| Forms                  | • BMC - Bulk Molding Compound                                                                                                                                            |

| Physical                                   | Nominal Value (English)           | Nominal Value (SI)             |             |
|--------------------------------------------|-----------------------------------|--------------------------------|-------------|
| Density / Specific Gravity                 | 1.70 to 1.85                      | 1.70 to 1.85 g/cm <sup>3</sup> |             |
| Mechanical                                 | Nominal Value (English)           | Nominal Value (SI)             | Test Method |
| Tensile Modulus (Compression Molded)       | 1.80E+6 psi                       | 12400 MPa                      | ASTM D638   |
| Tensile Strength (Compression Molded)      | 5500 psi                          | 37.9 MPa                       | ASTM D638   |
| Flexural Modulus (Compression Molded)      | 1.50E+6 psi                       | 10300 MPa                      | ASTM D790   |
| Flexural Strength (Compression Molded)     | 18000 psi                         | 124 MPa                        | ASTM D790   |
| Poisson's Ratio                            | 0.30                              | 0.30                           |             |
| Impact                                     | Nominal Value (English)           | Nominal Value (SI)             | Test Method |
| Notched Izod Impact (Compression Molded)   | 8.0 ft·lb/in                      | 430 J/m                        | ASTM D256   |
| Unnotched Izod Impact (Compression Molded) | 11 ft·lb/in                       | 590 J/m                        | ASTM D4812  |
| Thermal                                    | Nominal Value (English)           | Nominal Value (SI)             | Test Method |
| CLTE                                       |                                   |                                |             |
| Flow <sup>1</sup>                          | 1.4E-5 in/in/°F                   | 2.5E-5 cm/cm/°C                |             |
| Transverse <sup>2</sup>                    | 1.9E-5 in/in/°F                   | 3.5E-5 cm/cm/°C                |             |
| Thermal Conductivity                       | 2.1 Btu·in/hr/ft <sup>2</sup> /°F | 0.30 W/m/K                     |             |
| RTI Elec                                   | 266 °F                            | 130 °C                         | UL 746B     |
| RTI Imp                                    | 266 °F                            | 130 °C                         | UL 746B     |
| RTI Str                                    | 266 °F                            | 130 °C                         | UL 746B     |
| Electrical                                 | Nominal Value (English)           | Nominal Value (SI)             | Test Method |
| Dielectric Strength                        | 380 V/mil                         | 15 kV/mm                       | ASTM D149   |
| Arc Resistance                             | > 180 sec                         | > 180 sec                      | ASTM D495   |
| Comparative Tracking Index                 | 600 V                             | 600 V                          | ASTM D2303  |
| Flammability                               | Nominal Value (English)           | Nominal Value (SI)             | Test Method |
| Flame Rating (0.06 in (1.5 mm))            | V-0                               | V-0                            | UL 94       |

## Technical Data Sheet



### **Premi-glas 3100-22**

Thermoset, Unspecified  
LyondellBasell Industries  
Engineering Plastics



| Injection          | Nominal Value (English) | Nominal Value (SI) |
|--------------------|-------------------------|--------------------|
| Mold Temperature   | 300 °F                  | 149 °C             |
| Injection Pressure | 500 to 1000 psi         | 3.45 to 6.89 MPa   |

## Technical Data Sheet

**Premi-glas 3100-22**

Thermoset, Unspecified  
LyondellBasell Industries  
Engineering Plastics

**Notes**

<sup>1</sup> XY Direction

<sup>2</sup> Z Direction

**Notes**

These are typical property values not to be construed as specification limits.

**Processing Techniques**

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

**Product Storage and Handling**

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

**Company Information**

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

**Disclaimer**

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

**Trademarks**

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.