

Technical Data Sheet

Pro-fax HP553J

Polypropylene, Homopolymer



Product Description

Pro-fax HP553J is a low water carryover raffia and tape grade polypropylene homopolymer resin with a nominal MFR target of 3.5 g/10 min and good tensile strength. It is available in pellet form and is typically used in extrusion applications, including raffia, strapping, tapes, rope, twine and cordage.

Regulatory Status

For regulatory compliance information, see *Pro-fax* HP553J [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	North America
Application	Raffia/Tapes/Strapping; Ropes/Twine/Cordage
Processing Method	Cast Film
Attribute	Low Water Carryover

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	3.5	g/10 min	3.5	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm ³	0.90	g/cm ³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	222000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1530	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	5200	psi			ASTM D638
(50 mm/min)			35	MPa	ASTM D638
Tensile Elongation at Yield	10	%	10	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	0.97	ft-lb/in			ASTM D256
(23 °C, Method A)			52	J/m	ASTM D256

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.