



Purell HM671T

Polypropylene, Homopolymer

Product Description

Without exception, all potential activities for applications in the pharmaceutical, medical device, laboratory and diagnostics area have to be discussed with the relevant Technical (P & AD) and Business contacts first. To discuss a medical/pharmaceutical application please contact: your local Distributor or your local Basell contact. *Purell* HM671T is a high fluidity metallocene-catalysed polypropylene. It is nucleated and has a gamma – ray stabilizing additivition. *Purell* HM671T is a medical grade designed for injection moulding applications in medical after approval is given by Basell. *Purell* HM671T exhibits a very high stiffness combined with an excellent transparency and out-standing organoleptic properties. Its very narrow molecular weight distribution makes it particularly suitable for distortion-free mouldings. *Purell* HM671T is applied in high transparency and rigid pharmaceutical and diagnostic applications such as well and microtitre plates, measuring cups and labware.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	Europe
Processing Method	Injection Molding
Features	Homopolymer, Radiation Sterilizable, Autoclavable, Ethyleneoxide sterilisation, E-Beam Sterilizable
Typical Customer Applications	Medical Devices, Syringes, Diagnostic applications, Labware, Healthcare Applications

Typical Properties	Method	Value Unit
Physical		
Density (23°C)	ISO 1183	0.90 g/cm ³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	60 g/10 min
Melt volume flow rate (230°C/2.16kg)	ISO 1133	80 g/10 min
Mechanical		
Tensile Modulus (23 °C)	ISO 527-1, -2	1700 MPa
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	33 MPa
Tensile Strain at Break (23 °C)	ISO 527-1, -2	>50 %
Tensile Strain at Yield (23 °C)	ISO 527-1, -2	9 %
Flexural modulus (23 °C)	ISO 178	1550 MPa
Impact		
Notched izod impact strength	ISO 180	
(+23 °C)		3 kJ/m ²
(0 °C)		2 kJ/m ²
(-20 °C)		1 kJ/m ²
Hardness		
Ball indentation hardness ((H358/30))	ISO 2039-1	73 MPa
Thermal		
Vicat softening temperature A/50	ISO 306	135 °C
Vicat softening temperature B/50	ISO 306	87 °C
Heat deflection temperature B	ISO 75/ASTM D 648	94 °C
Optical		
Haze (1 mm)	ASTM D 1003	10 %

Notes

Typical properties; not to be construed as specifications.

Further Information

Purell HM671T

Conveying: Conveying equipment should be designed to prevent production and accumulation of fines and dust particles that are contained in polymer resins. These particles can under certain conditions pose an explosion hazard. We recommend the conveying system used is equipped with adequate filters, is operated and maintained that no leak develops and adequate grounding exists at all times.

Health and Safety:

The resin is manufactured to the highest standards but, special requirements apply to certain applications such as food end-use contact and direct medical use. For specific information on regulatory compliance contact your local representative.

Workers should be protected from the possibility of skin or eye contact with molten polymer.

Safety glasses are suggested as a minimal precaution to prevent mechanical or thermal injury to the eyes.

Molten polymer may be degraded if it is exposed to air during any of the processing and off-line operations. The products of degradation have an unpleasant odour. In higher concentrations they may cause irritation of the mucus membranes. Fabrication areas should be ventilated to carry away fumes or vapours. Legislation on the control of emissions and pollution prevention must be observed. If the principles of sound manufacturing practice are adhered to and the place of work is well ventilated, no health hazards are involved in processing the resin.

The resin will burn when supplied with excess heat and oxygen. It should be handled and stored away from contact with direct flames and/or ignition sources. In burning the resin contributes high heat and may generate a dense black smoke. Starting fires can be extinguished by water, developed fires should be extinguished by heavy foams forming an aqueous or polymeric film. For further information about safety in handling and processing please refer to the Material Safety Data Sheet.

Storage:

The resin is packed in 25 kg bags or in bulk containers protecting it from contamination. If it is stored under adverse conditions, i. e. if there are large fluctuations in ambient temperature and the atmospheric humidity is high, moisture may condense inside the packaging. Under these circumstances, it is recommended to dry the resin before use. Unfavourable storage conditions may also intensify the resin's slight characteristic odour.

The resin is subjected to degradation by ultra-violet radiations or by high storage temperatures. Therefore the resin must be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. The resin can be stored over a period of more than 6 month without significant changes in the specified properties, appropriate storage conditions provided. Higher storage temperatures reduce the storage time.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. The data do not relieve the customer from his obligation to control the resin upon arrival and to complain about faults. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

© LyondellBasell Industries Holdings, B.V. 2010

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product(s) may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application.

Users should review the applicable Material Safety Data Sheet before handling the product.

Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Aquamarine, Aquathene, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Duotreat, Filmex, Flexathene, Get in touch with, Glacido, Glidox, Glidsol, Hifax, Histif, Hostacom, Hostalen PP, Hostalen ACP, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupocomp, Lupolen, Lupolex, Luposim, Lupo stress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Navacet, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-Fax, Punctilious, Purell, SAA 100, SAA 101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, Tetralol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido, Valtec, and Winsense are trademarks owned and/or used by LyondellBasell group companies.

Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Filmex, Flexathene, Glidox, Glidsol, Hifax, Hostacom, Hostalen, Ideal, Indure, Integrate, Koattro, Lucalen, Lupolen, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-Fax, Punctilious, Purell, Sequel, Spheripol, Spherizone, Softell, Starflex, Tebol, Tetralol, T-Hydro, Toppyl, Tufflo, Ultrathene, and Winsense are registered in the U.S. Patent and Trademark Office.

Release Date: 30 Nov 2010