

Technical Data Sheet

**Qr Resin PC/ABS-1015**

Polycarbonate
LyondellBasell Industries
Engineering Plastics

Product Description

Available with UV (V) or Release (R).

General

Material Status	• Commercial: Active				
Availability	• North America				
Features	• High Impact Resistance				
Appearance	• Colors Available	• Natural Color			
Forms	• Pellets				
Processing Method	• Injection Molding				

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.20	1.20 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15 g/10 min	15 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	9000 psi	62.1 MPa	ASTM D638
Flexural Modulus	330000 psi	2280 MPa	ASTM D790
Flexural Strength (Yield)	13000 psi	89.6 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	12 ft-lb/in	640 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	275 °F	135 °C	
264 psi (1.8 MPa), Unannealed	260 °F	127 °C	

Technical Data Sheet



Qr Resin PC/ABS-1015

Polycarbonate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	4.0 to 8.0 hr	4.0 to 8.0 hr
Drying Time, Maximum	8.0 hr	8.0 hr
Rear Temperature	490 to 530 °F	254 to 277 °C
Middle Temperature	510 to 570 °F	266 to 299 °C
Front Temperature	530 to 570 °F	277 to 299 °C
Nozzle Temperature	520 to 560 °F	271 to 293 °C
Processing (Melt) Temp	520 to 560 °F	271 to 293 °C
Mold Temperature	160 to 200 °F	71 to 93 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.