

Technical Data Sheet



Qr Resin QR-1000-GF20

Polycarbonate
LyondellBasell Industries
Engineering Plastics

Product Description

Available with UV (V) or Release (R).

General

Material Status	• Commercial: Active		
Availability	• North America		
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Features	• Good Toughness		
Appearance	• Colors Available	• Natural Color	
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.35	1.35 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10 to 20 g/10 min	10 to 20 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	16000 psi	110 MPa	ASTM D638
Flexural Modulus	780000 psi	5380 MPa	ASTM D790
Flexural Strength (Yield)	18800 psi	130 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Unnotched Izod Impact (73°F (23°C))	18 ft-lb/in	960 J/m	ASTM D4812
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	300 °F	149 °C	
264 psi (1.8 MPa), Unannealed	295 °F	146 °C	

Technical Data Sheet



Qr Resin QR-1000-GF20

Polycarbonate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	3.0 to 6.0 hr	3.0 to 6.0 hr
Drying Time, Maximum	6.0 hr	6.0 hr
Rear Temperature	540 to 590 °F	282 to 310 °C
Middle Temperature	560 to 600 °F	293 to 316 °C
Front Temperature	580 to 620 °F	304 to 327 °C
Nozzle Temperature	580 to 610 °F	304 to 321 °C
Processing (Melt) Temp	580 to 620 °F	304 to 327 °C
Mold Temperature	180 to 240 °F	82 to 116 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.