

Technical Data Sheet

**Qr Resin QR-1000-GFR40**

Polycarbonate
LyondellBasell Industries
Engineering Plastics

Product Description

Available with UV (V) or Release (R).
Flame Packages Available (0.0625 in min. thickness): 94V-2, 94V-0, 94-5VA

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight
Features	• Good Toughness
Appearance	• Colors Available • Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.53	1.53 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10 to 20 g/10 min	10 to 20 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	22500 psi	155 MPa	ASTM D638
Flexural Modulus	1.38E+6 psi	9510 MPa	ASTM D790
Flexural Strength (Yield)	26000 psi	179 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Unnotched Izod Impact (73°F (23°C))	20 ft·lb/in	1100 J/m	ASTM D4812
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	310 °F	154 °C	
264 psi (1.8 MPa), Unannealed	295 °F	146 °C	

Technical Data Sheet



Qr Resin QR-1000-GFR40

Polycarbonate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	3.0 to 6.0 hr	3.0 to 6.0 hr
Drying Time, Maximum	6.0 hr	6.0 hr
Rear Temperature	560 to 600 °F	293 to 316 °C
Middle Temperature	580 to 620 °F	304 to 327 °C
Front Temperature	600 to 640 °F	316 to 338 °C
Nozzle Temperature	590 to 630 °F	310 to 332 °C
Processing (Melt) Temp	600 to 640 °F	316 to 338 °C
Mold Temperature	180 to 240 °F	82 to 116 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.