

Technical Data Sheet

**Qr Resin QR-2000-GF30**

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

General			
Material Status	• Commercial: Active		
Availability	• North America		
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• High Heat Resistance		
Appearance	• Colors Available	• Grey	
Forms	• Pellets		
Processing Method	• Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.20	1.20 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Break)	15000 psi	103 MPa	ASTM D638
Tensile Elongation (Break)	1.2 %	1.2 %	ASTM D638
Flexural Modulus	1.09E+6 psi	7520 MPa	ASTM D790
Flexural Strength (Break)	24000 psi	165 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.80 ft·lb/in	43 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	220 °F	104 °C	
264 psi (1.8 MPa), Unannealed	210 °F	98.9 °C	

Technical Data Sheet



Qr Resin QR-2000-GF30

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	200 °F	93 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Drying Time, Maximum	4.0 hr	4.0 hr
Rear Temperature	370 to 410 °F	188 to 210 °C
Middle Temperature	400 to 440 °F	204 to 227 °C
Front Temperature	420 to 460 °F	216 to 238 °C
Nozzle Temperature	420 to 500 °F	216 to 260 °C
Processing (Melt) Temp	420 to 500 °F	216 to 260 °C
Mold Temperature	120 to 160 °F	49 to 71 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.