

Technical Data Sheet

**Qr Resin QR-8000-GF20**

Polybutylene Terephthalate
LyondellBasell Industries
Engineering Plastics

Product Description

QR-8000-GF20 is available with Lubricant (L).

General

Material Status	• Commercial: Active		
Availability	• North America		
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Additive	• Lubricant		
Features	• Good Dimensional Stability • High Stiffness	• High Strength • Lubricated	
Appearance	• Black	• Colors Available	• Natural Color
Forms	• Pellets		

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	14500 psi	100 MPa	ASTM D638
Tensile Elongation (Yield)	2.7 %	2.7 %	ASTM D638
Flexural Modulus	800000 psi	5520 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.1 ft-lb/in	59 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	400 °F	204 °C	ASTM D648

Technical Data Sheet



Qr Resin QR-8000-GF20

Polybutylene Terephthalate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	3.0 to 6.0 hr	3.0 to 6.0 hr
Drying Time, Maximum	6.0 hr	6.0 hr
Suggested Max Moisture	0.02 %	0.02 %
Rear Temperature	460 to 490 °F	238 to 254 °C
Middle Temperature	470 to 500 °F	243 to 260 °C
Front Temperature	480 to 510 °F	249 to 266 °C
Nozzle Temperature	470 to 500 °F	243 to 260 °C
Processing (Melt) Temp	480 to 520 °F	249 to 271 °C
Mold Temperature	150 to 200 °F	66 to 93 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.