

Technical Data Sheet



Schulablend (ABS/PA) M/MK 6501 U

Acrylonitrile Butadiene Styrene + PA

LyondellBasell Industries

Engineering Plastics

Product Description

ABS/PA6 blend with high impact strength, UV stabilised, low emission. (Former name: SCHULABLEND® M/MK K2004)

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• UV Stabilizer		
Features	• Good Flow	• High Impact Resistance	
Processing Method	• Injection Molding		
Part Marking Code (ISO 11469)	• >ABS+PA<		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.07 g/cm ³	1.07 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (250°C/5.0 kg)	7.0 cm ³ /10min	7.0 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	247000 psi	1700 MPa	ISO 527-1/1
Tensile Stress			ISO 527-2/1A/50
Yield	5800 psi	40.0 MPa	
Break	6090 psi	42.0 MPa	
Tensile Strain (Yield)	4.0 %	4.0 %	ISO 527-2/1A/50
Nominal Tensile Strain at Break	90 %	90 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	9.5 ft·lb/in ²	20 kJ/m ²	
73°F (23°C)	38 ft·lb/in ²	80 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ISO 75-2/Af
264 psi (1.8 MPa), Unannealed	149 °F	65.0 °C	
Vicat Softening Temperature	257 °F	125 °C	ISO 306/B50
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.6 mm)	HB	HB	

Additional Information

The tradename "Schulablend" may be abbreviated "SBL" in documents or on labels.

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet



Schulablend (ABS/PA) M/MK 6501 U

Acrylonitrile Butadiene Styrene + PA
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 hr	4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	446 to 518 °F	230 to 270 °C
Mold Temperature	104 to 176 °F	40 to 80 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.