

Technical Data Sheet

**Schulablend (PC/ASA) M/MA 6402 U**

Polycarbonate + ASA
LyondellBasell Industries
Engineering Plastics

Product Description

PC-ASA blend with increased impact strength, heat resistance and weather resistance.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Impact Resistance	• Good Weather Resistance	• High Heat Resistance
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PC+ASA UV		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.15 g/cm ³	1.15 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	28 cm ³ /10min	28 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	334000 psi	2300 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	6960 psi	48.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	4.5 %	4.5 %	ISO 527-2/1A/50
Flexural Modulus ¹	363000 psi	2500 MPa	ISO 178
Flexural Stress ¹ (3.5% Strain)	11600 psi	80.0 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	7.1 ft·lb/in ²	15 kJ/m ²	
73°F (23°C)	24 ft·lb/in ²	50 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	248 °F	120 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	212 °F	100 °C	ISO 75-2/ Af
Vicat Softening Temperature	266 °F	130 °C	ISO 306/B50
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	

Technical Data Sheet

**Schulablend (PC/ASA) M/MA 6402 U**

Polycarbonate + ASA
LyondellBasell Industries
Engineering Plastics

Additional Information

The tradename "Schulablend" may be abbreviated "SBL" in documents or on labels.

Characteristic properties

Retaining good impact-strength to low temperatures, PC-ASA blend also possess high rigidity, hardness and high heat deflection. Additional to this the material is highly UV resistant. Material has a glossy appearance.

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet



Schulablend (PC/ASA) M/MA 6402 U

Polycarbonate + ASA
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	212 °F	100 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Max Moisture	0.02 %	0.02 %
Hopper Temperature	158 °F	70 °C
Rear Temperature	482 °F	250 °C
Middle Temperature	518 °F	270 °C
Front Temperature	554 °F	290 °C
Processing (Melt) Temp	500 to 554 °F	260 to 290 °C
Mold Temperature	140 to 194 °F	60 to 90 °C
Injection Pressure	11600 to 21800 psi	80.0 to 150 MPa
Injection Rate	Fast	Fast
Holding Pressure	4350 to 10900 psi	30.0 to 75.0 MPa
Back Pressure	725 to 2180 psi	5.00 to 15.0 MPa
Cushion	0.0787 to 0.197 in	2.00 to 5.00 mm
Screw Speed	1 in/min	24 mm/min

Injection Notes

Predrying

Predrying should effect a moisture content of 0,02%, otherwise you get material degradation and bubbles. Typically predrying at 100°C for ca. 4-6 hours is recommended in a dehumidifying dryer.

Reprocessing

Recycle content 10 - 20%. Use only well dried regrind. It should be tested if parts made with regrind material fulfil the part specifications.

Shut down

For long breaks don't shut off the machine but reduce the temperature to 180°C. Otherwise purge with polyolefines or SAN.

Finishing

(PC/ASA) is suitable for machining. Varnishing, printing, gluing and embossing can be carried out using commercially available products.

Technical Data Sheet

**Schulablend (PC/ASA) M/MA 6402 U**

Polycarbonate + ASA
LyondellBasell Industries
Engineering Plastics

Notes

¹ 0.079 in/min (2.0 mm/min)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.