

Technical Data Sheet



Schuladur A GF 30

Polybutylene Terephthalate
LyondellBasell Industries
Engineering Plastics

Product Description

30% glass fibre reinforced PBT compound

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Asia Pacific	• Europe
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Medium Viscosity		
Automotive Specifications	• FORD WSK-M4D725-A Color: Black	• GM QK 006615 Color: 96.8001 Black	
UL File Number	• E86615		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PBT-GF		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.53 g/cm ³	1.53 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	18 cm ³ /10min	18 cm ³ /10min	ISO 1133
Water Absorption Equilibrium, 73°F (23°C), 50% RH	0.30 %	0.30 %	ISO 62
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.45E+6 psi	10000 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	18900 psi	130 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.5 %	2.5 %	ISO 527-2/1A/5
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength -22°F (-30°C)	2.4 ft·lb/in ²	5.0 kJ/m ²	ISO 179/1eA
73°F (23°C)	3.8 ft·lb/in ²	8.0 kJ/m ²	
Charpy Unnotched Impact Strength -22°F (-30°C)	26 ft·lb/in ²	55 kJ/m ²	ISO 179/1eU
73°F (23°C)	29 ft·lb/in ²	60 kJ/m ²	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	33100 psi	228 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed	419 °F	215 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	401 °F	205 °C	ISO 75-2/Af
Vicat Softening Temperature --	415 °F	213 °C	ISO 306/B50
--	424 °F	218 °C	ISO 306/A50
Ball Pressure Test (392°F (200°C))	Pass	Pass	IEC 60695-10-2
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index	350 V	350 V	IEC 60112
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate 0.0787 in (2.00 mm)	1.5 in/min	39 mm/min	ISO 3795
0.0787 in (2.00 mm)	1.5 in/min	39 mm/min	FMVSS 302

Technical Data Sheet

**Schuladur A GF 30**

Polybutylene Terephthalate
LyondellBasell Industries
Engineering Plastics


Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.030 in (0.75 mm)	HB	HB	
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in (1.5 mm)	1380 °F	750 °C	
0.12 in (3.0 mm)	1380 °F	750 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 in (1.5 mm)	1430 °F	775 °C	
0.12 in (3.0 mm)	1430 °F	775 °C	
Oxygen Index	19 %	19 %	ISO 4589-2
Additional Information			
1.) Not for use in food contact applications			
2.) Not for use in medical or pharmaceutical applications			

Technical Data Sheet



Schuladur A GF 30

Polybutylene Terephthalate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	248 °F	120 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.05 %	0.05 %
Processing (Melt) Temp	482 to 500 °F	250 to 260 °C
Mold Temperature	158 to 194 °F	70 to 90 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.