

Technical Data Sheet

**Schuladur A2 GF 15 K1882 LS**

Polybutylene Terephthalate + ASA

LyondellBasell Industries

Engineering Plastics

Product Description

15% glass fibre reinforced PBT/ASA-blend with high surface and reduced warpage

General

Material Status	• Commercial: Active
Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• (PBT+ASA)-GF15

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.31 g/cm ³	1.31 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR)			ISO 1133
250°C/2.16 kg	5.0 cm ³ /10min	5.0 cm ³ /10min	
250°C/5.0 kg	30 cm ³ /10min	30 cm ³ /10min	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	674000 psi	4650 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	8700 psi	60.0 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.2 %	3.2 %	ISO 527-2/1A/5
Flexural Modulus (73°F (23°C))	595000 psi	4100 MPa	ISO 178
Flexural Stress (73°F (23°C))	13600 psi	94.0 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	2.9 ft·lb/in ²	6.0 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
73°F (23°C)	19 ft·lb/in ²	40 kJ/m ²	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	392 °F	200 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	266 °F	130 °C	ISO 75-2/ Af
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Comparative Tracking Index	250 V	250 V	IEC 60112
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet



Schuladur A2 GF 15 K1882 LS

Polybutylene Terephthalate + ASA
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	212 °F	100 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.05 %	0.05 %
Hopper Temperature	158 °F	70 °C
Rear Temperature	446 °F	230 °C
Middle Temperature	473 °F	245 °C
Front Temperature	500 °F	260 °C
Nozzle Temperature	500 °F	260 °C
Processing (Melt) Temp	482 to 500 °F	250 to 260 °C
Mold Temperature	140 to 194 °F	60 to 90 °C
Injection Pressure	11600 to 17400 psi	80.0 to 120 MPa
Holding Pressure	5800 to 10200 psi	40.0 to 70.0 MPa
Back Pressure	725 to 1450 psi	5.00 to 10.0 MPa
Vent Depth	7.9E-4 in	0.020 mm
Screw Speed	709 in/min	18 m/min

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Page: 2 of 3
LyondellBasell

www.lyondellbasell.com
Publish Date: 2024-03-14

Technical Data Sheet

**Schuladur A2 GF 15 K1882 LS**

Polybutylene Terephthalate + ASA
LyondellBasell Industries
Engineering Plastics

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.