

Technical Data Sheet



Schulaform AF 9 natur

Acetal (POM) Copolymer
LyondellBasell Industries
Engineering Plastics

Product Description

Aramid fibre filled POM compound with improved wear and friction behaviour

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific	• Europe
Filler / Reinforcement	• Aramid Fiber	
Features	• Wear Resistant	
Automotive Specifications	• GM QK 000367 Type A Color: Natural	• IMDS ID 17340386 Color: Natural
Processing Method	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.41 g/cm ³	1.41 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	6.0 cm ³ /10min	6.0 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	392000 psi	2700 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	7980 psi	55.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	10 %	10 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	2.6 ft·lb/in ²	5.5 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength 73°F (23°C)	21 ft·lb/in ²	45 kJ/m ²	ISO 179/1eU
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	203 °F	95.0 °C	ISO 75-2/Af
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification 0.06 in (1.6 mm)	HB	HB	IEC 60695-11-10, -20

Technical Data Sheet



Schulaform AF 9 natur

Acetal (POM) Copolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	212 °F	100 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	392 to 410 °F	200 to 210 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.