

Technical Data Sheet



Schulaketon MV

Polyketone, Aliphatic
LyondellBasell Industries
Engineering Plastics

Product Description

Medium viscosity aliphatic Polyketone

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Processing Method	• Extrusion • Injection Molding		
Resin ID (ISO 1043)	• PK		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.24 g/cm ³	1.24 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (240°C/2.16 kg)	6.0 cm ³ /10min	6.0 cm ³ /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	232000 psi	1600 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	8700 psi	60.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	20 %	20 %	ISO 527-2/1A/50
Flexural Modulus ¹	247000 psi	1700 MPa	ISO 178
Flexural Stress ¹			ISO 178
9.0% Strain	8700 psi	60.0 MPa	
3.5% Strain	8700 psi	60.0 MPa	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°F (-40°C)	1.4 ft·lb/in ²	3.0 kJ/m ²	
73°F (23°C)	7.6 ft·lb/in ²	16 kJ/m ²	
Charpy Unnotched Impact Strength			
-40°F (-40°C)	No Break	No Break	ISO 179
73°F (23°C)	No Break	No Break	ISO 179/1eU
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	352 °F	178 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	181 °F	83.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	369 °F	187 °C	ISO 306/B50
--	417 °F	214 °C	ISO 306/A50
RTI Elec			UL 746B
0.031 in (0.8 mm)	122 °F	50.0 °C	
0.06 in (1.6 mm)	122 °F	50.0 °C	
0.12 in (3.0 mm)	122 °F	50.0 °C	
RTI Imp			UL 746B
0.031 in (0.8 mm)	122 °F	50.0 °C	
0.06 in (1.6 mm)	122 °F	50.0 °C	
0.12 in (3.0 mm)	122 °F	50.0 °C	
RTI Str			UL 746B
0.031 in (0.8 mm)	122 °F	50.0 °C	
0.06 in (1.6 mm)	122 °F	50.0 °C	
0.12 in (3.0 mm)	122 °F	50.0 °C	

Technical Data Sheet



Schulaketon MV

Polyketone, Aliphatic
LyondellBasell Industries
Engineering Plastics


Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index (Solution A)	600 V	600 V	IEC 60112
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flame Rating			
0.031 in (0.8 mm)	HB	HB	UL 94
0.06 in (1.6 mm)	HB	HB	UL 94 IEC 60695-11-10, -20
0.13 in (3.2 mm)	HB	HB	UL 94
0.03 in (0.8 mm)	HB	HB	IEC 60695-11-10, -20
0.12 in (3.0 mm)	HB	HB	IEC 60695-11-10, -20
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in (1.5 mm)	1290 °F	700 °C	
0.12 in (3.0 mm)	1290 °F	700 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 in (1.5 mm)	1340 °F	725 °C	
0.12 in (3.0 mm)	1340 °F	725 °C	

Technical Data Sheet



Schulaketon MV

Polyketone, Aliphatic
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.15 %	0.15 %
Processing (Melt) Temp	437 to 464 °F	225 to 240 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

Injection Notes

Before start, nozzle, screw, barrel and hot-runner have to be cleaned with Polyolefin. Contamination of other material leads to degradation or crosslinking of SCHULAKETON®.

Avoid shut down for more than 15 minutes at moulding temperature, because of degradation and crosslinking of SCHULAKETON®. Purge with Polyolefin!

Technical Data Sheet



Schulaketon MV

Polyketone, Aliphatic
LyondellBasell Industries
Engineering Plastics

Notes

¹ 0.079 in/min (2.0 mm/min)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.