

Technical Data Sheet



Schulamid 6 GF 30 FR 4

Polyamide 6
LyondellBasell Industries
Engineering Plastics

Product Description

30% glass fibre reinforced flame-retardant halogenated Polyamide 6 grade; without PBDE

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Flame Retardant	• Good Strength	
UL File Number	• E86615		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PA6 GF30 FR(17)		

Physical	Dry	Conditioned	Unit	Test Method
Density	1.55	--	g/cm ³	ISO 1183/A
Viscosity Number	145	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.38E+6 (9500)	986000 (6800)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	22500 (155)	15500 (107)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	2.5	5.2	%	ISO 527-2/1A/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	2.9 (6.0)	--	ft-lb/in ² (kJ/m ²)	
73°F (23°C)	4.8 (10)	6.2 (13)	ft-lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	28 (58)	--	ft-lb/in ² (kJ/m ²)	
73°F (23°C)	31 (65)	35 (74)	ft-lb/in ² (kJ/m ²)	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 358/30)	29000 (200)	--	psi (MPa)	ISO 2039-1
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 psi (0.45 MPa), Unannealed	421 (216)	--	°F (°C)	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	396 (202)	--	°F (°C)	ISO 75-2/Af
Ball Pressure Test (392°F (200°C))	Pass	--		IEC 60695-10-2
RTI Elec				UL 746B
0.030 in (0.75 mm)	149 (65.0)	--	°F (°C)	
0.06 in (1.5 mm)	149 (65.0)	--	°F (°C)	
0.12 in (3.0 mm)	149 (65.0)	--	°F (°C)	

Technical Data Sheet


Schulamid 6 GF 30 FR 4

Polyamide 6
LyondellBasell Industries
Engineering Plastics

Thermal	Dry	Conditioned	Unit	Test Method
RTI Imp				UL 746B
0.030 in (0.75 mm)	149 (65.0)	--	°F (°C)	
0.06 in (1.5 mm)	149 (65.0)	--	°F (°C)	
0.12 in (3.0 mm)	149 (65.0)	--	°F (°C)	
RTI Str				UL 746B
0.030 in (0.75 mm)	149 (65.0)	--	°F (°C)	
0.06 in (1.5 mm)	149 (65.0)	--	°F (°C)	
0.12 in (3.0 mm)	149 (65.0)	--	°F (°C)	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+15	> 1.0E+12	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	> 1.0E+10	ohms·m	IEC 62631-3-1
Comparative Tracking Index	250	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746A
0.030 in (0.75 mm)	PLC 0	--		
0.06 in (1.5 mm)	PLC 0	--		
0.12 in (3.0 mm)	PLC 0	--		
Hot-wire Ignition (HWI)				UL 746A
0.030 in (0.75 mm)	PLC 0	--		
0.06 in (1.5 mm)	PLC 0	--		
0.12 in (3.0 mm)	PLC 0	--		
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				ISO 3795
0.0295 in (0.750 mm), Self-Extinguishing	0.0	--	in/min (mm/min)	
0.0591 in (1.50 mm), Self-Extinguishing	0.0	--	in/min (mm/min)	
0.118 in (3.00 mm), Self-Extinguishing	0.0	--	in/min (mm/min)	
Flame Rating				UL 94 IEC 60695-11-10, -20
0.030 in (0.75 mm)	V-0	--		
0.06 in (1.5 mm)	V-0	--		
0.12 in (3.0 mm)	V-0	--		

Technical Data Sheet**Schulamid 6 GF 30 FR 4**

Polyamide 6
LyondellBasell Industries
Engineering Plastics


Flammability	Dry	Conditioned	Unit	Test Method
Glow Wire Flammability Index				IEC 60695-2-12
0.030 in (0.75 mm)	1760 (960)	--	°F (°C)	
0.06 in (1.5 mm)	1760 (960)	--	°F (°C)	
0.12 in (3.0 mm)	1760 (960)	--	°F (°C)	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.030 in (0.75 mm)	1520 (825)	--	°F (°C)	
0.06 in (1.5 mm)	1520 (825)	--	°F (°C)	
0.12 in (3.0 mm)	1520 (825)	--	°F (°C)	
Oxygen Index	30	--	%	ISO 4589-2

Technical Data Sheet



Schulamid 6 GF 30 FR 4

Polyamide 6
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	464 to 518 °F	240 to 270 °C
Mold Temperature	140 to 212 °F	60 to 100 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Screw Speed	< 591 in/min	< 15 m/min

Injection Notes

Mould surface contacting melt should be of non-corrosive steel (content of chrome > 12%)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.