

Technical Data Sheet



Schulamid 66 GBF 3020 FR 4

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Product Description

30% glass fibre and glass beads reinforced flame-retardant Polyamide 66 grade with low warpage high mechanical stability and high dimension stability, without PBDE

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Bead\Glass Fiber, 30% Filler by Weight		
Features	• Flame Retardant	• Low Warpage	
UL File Number	• E86615		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PA66 (GF+GB)30 FR(17)		

Physical	Dry	Conditioned	Unit	Test Method
Density	1.59	--	g/cm ³	ISO 1183/A
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.26E+6 (8700)	725000 (5000)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	20300 (140)	13300 (92.0)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	2.5	4.5	%	ISO 527-2/1A/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	2.1 (4.5)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	2.6 (5.5)	3.3 (7.0)	ft·lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	18 (38)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	20 (42)	24 (51)	ft·lb/in ² (kJ/m ²)	

Technical Data Sheet


Schulamid 66 GBF 3020 FR 4

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 psi (0.45 MPa), Unannealed	> 482 (> 250)	--	°F (°C)	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	435 (224)	--	°F (°C)	ISO 75-2/Af
Ball Pressure Test (392°F (200°C))	Pass	--		IEC 60695-10-2
RTI Elec				UL 746B
0.06 in (1.5 mm)	149 (65.0)	--	°F (°C)	
0.12 in (3.0 mm)	149 (65.0)	--	°F (°C)	
RTI Imp				UL 746B
0.06 in (1.5 mm)	149 (65.0)	--	°F (°C)	
0.12 in (3.0 mm)	149 (65.0)	--	°F (°C)	
RTI Str				UL 746B
0.06 in (1.5 mm)	149 (65.0)	--	°F (°C)	
0.12 in (3.0 mm)	149 (65.0)	--	°F (°C)	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 7.8E+12	--	ohms	IEC 60093
Volume Resistivity	> 9.9E+13	--	ohms·m	IEC 62631-3-1
Electric Strength	560 (22)	--	V/mil (kV/mm)	IEC 60243-1
Relative Permittivity				IEC 60250
100 Hz	4.81	--		
1 MHz	3.85	--		
Dissipation Factor				IEC 60250
100 Hz	0.049	--		
1 MHz	0.022	--		
Comparative Tracking Index (Solution A)	175	--	V	IEC 60112

Technical Data Sheet


Schulamid 66 GBF 3020 FR 4

Polyamide 66
LyondellBasell Industries
Engineering Plastics


Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				ISO 3795
0.0787 in (2.00 mm), Self-Extinguishing	0.0	--	in/min (mm/min)	
Flame Rating				UL 94 IEC 60695-11-10, -20
0.06 in (1.5 mm)	V-0	--		
0.12 in (3.0 mm)	V-0	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.06 in (1.5 mm)	1760 (960)	--	°F (°C)	
0.12 in (3.0 mm)	1760 (960)	--	°F (°C)	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.06 in (1.5 mm)	1380 (750)	--	°F (°C)	
0.12 in (3.0 mm)	1380 (750)	--	°F (°C)	
Oxygen Index	38	--	%	ISO 4589-2

Technical Data Sheet



Schulamid 66 GBF 3020 FR 4

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	518 to 572 °F	270 to 300 °C
Mold Temperature	140 to 194 °F	60 to 90 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Screw Speed	< 591 in/min	< 15 m/min

Injection Notes

Mould surface contacting melt should be of non-corrosive steel (content of chrome > 12%)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.