

Technical Data Sheet



Schulamid 66 GF30 H2 FR2

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Product Description

30% glass fibre reinforced flame-retardant Polyamide 66 grade; halogen free, electrically neutral heat stabilized

General

Material Status	• Experimental: Active
Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Electrical Corrosion Resistant • Flame Retardant • Halogen Free • Heat Stabilized
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66 GF30 FR(40)

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.44 g/cm ³	1.44 g/cm ³	ISO 1183/A
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.67E+6 psi	11500 MPa	ISO 527-1/1A
Tensile Stress (Break)	20300 psi	140 MPa	ISO 527-2/1A
Tensile Strain (Break)	2.4 %	2.4 %	ISO 527-2/1A
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	4.8 ft·lb/in ²	10 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength 73°F (23°C)	31 ft·lb/in ²	65 kJ/m ²	ISO 179/1eU
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	493 °F	256 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	468 °F	242 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	444 °F	229 °C	ISO 306/B50
--	491 °F	255 °C	ISO 306/A50
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Comparative Tracking Index	600 V	600 V	IEC 60112
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			ISO 3795
0.0295 in (0.750 mm), Self-Extinguishing	0.0 in/min	0.0 mm/min	
0.0591 in (1.50 mm), Self-Extinguishing	0.0 in/min	0.0 mm/min	
0.118 in (3.00 mm), Self-Extinguishing	0.0 in/min	0.0 mm/min	
Flammability Classification			IEC 60695-11-10, -20
0.030 in (0.75 mm)	V-0	V-0	
0.06 in (1.5 mm)	V-0	V-0	
0.12 in (3.0 mm)	V-0	V-0	
Glow Wire Flammability Index			IEC 60695-2-12
0.030 in (0.75 mm)	1760 °F	960 °C	
0.06 in (1.5 mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.030 in (0.75 mm)	1380 °F	750 °C	
0.06 in (1.5 mm)	1380 °F	750 °C	

Technical Data Sheet



Schulamid 66 GF30 H2 FR2

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	518 to 572 °F	270 to 300 °C
Mold Temperature	140 to 212 °F	60 to 100 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Screw Speed	< 591 in/min	< 15 m/min

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.