

Technical Data Sheet



Schulamid 66 MV 5 FR

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Product Description

Medium viscosity flame-retardant Polyamide 66 grade, V-0 by 0,38 mm; halogen free

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Antimony Free • Flame Retardant	• Halogen Free • Low Smoke Emission	
UL File Number	• E86615		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PA66 FR(30)		

Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183/A
Viscosity Number	152	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	522000 (3600)	261000 (1800)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Yield)	11600 (80.0)	7980 (55.0)	psi (MPa)	ISO 527-2/1A/50
Tensile Strain (Yield)	4.9	18	%	ISO 527-2/1A/50
Flexural Modulus ¹	537000 (3700)	--	psi (MPa)	ISO 178
Flexural Stress				ISO 178
6.3% Strain	18900 (130)	--	psi (MPa)	
3.5% Strain ¹	16700 (115)	--	psi (MPa)	
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	1.4 (3.0)	--	ft-lb/in ² (kJ/m ²)	
73°F (23°C)	2.4 (5.0)	5.7 (12)	ft-lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	12 (25)	--	ft-lb/in ² (kJ/m ²)	
73°F (23°C)	33 ft-lb/in ² (70 kJ/m ²)	No Break	(kJ/m ²)	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 psi (0.45 MPa), Unannealed	432 (222)	--	°F (°C)	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	176 (80.0)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature				
--	460 (238)	--	°F (°C)	ISO 306/B50
--	482 (250)	--	°F (°C)	ISO 306/A50

Technical Data Sheet


Schulamid 66 MV 5 FR

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Thermal	Dry	Conditioned	Unit	Test Method
Ball Pressure Test (257°F (125°C))	Pass	--		IEC 60695-10-2
RTI Elec				UL 746B
0.015 in (0.38 mm)	284 (140)	--	°F (°C)	
0.030 in (0.75 mm)	284 (140)	--	°F (°C)	
0.04 in (1.0 mm)	302 (150)	--	°F (°C)	
0.06 in (1.5 mm)	302 (150)	--	°F (°C)	
0.12 in (3.0 mm)	302 (150)	--	°F (°C)	
RTI Imp				UL 746B
0.015 in (0.38 mm)	221 (105)	--	°F (°C)	
0.030 in (0.75 mm)	239 (115)	--	°F (°C)	
0.04 in (1.0 mm)	239 (115)	--	°F (°C)	
0.06 in (1.5 mm)	239 (115)	--	°F (°C)	
0.12 in (3.0 mm)	239 (115)	--	°F (°C)	
RTI Str				UL 746B
0.015 in (0.38 mm)	212 (100)	--	°F (°C)	
0.030 in (0.75 mm)	230 (110)	--	°F (°C)	
0.04 in (1.0 mm)	230 (110)	--	°F (°C)	
0.06 in (1.5 mm)	230 (110)	--	°F (°C)	
0.12 in (3.0 mm)	230 (110)	--	°F (°C)	
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746A
0.015 in (0.38 mm)	PLC 1	--		
0.030 in (0.75 mm)	PLC 1	--		
0.04 in (1.0 mm)	PLC 1	--		
0.06 in (1.5 mm)	PLC 0	--		
0.12 in (3.0 mm)	PLC 0	--		

Technical Data Sheet


Schulamid 66 MV 5 FR

Polyamide 66
LyondellBasell Industries
Engineering Plastics


Electrical	Dry	Conditioned	Unit	Test Method
Hot-wire Ignition (HWI)				UL 746A
0.015 in (0.38 mm)	PLC 4	--		
0.030 in (0.75 mm)	PLC 4	--		
0.04 in (1.0 mm)	PLC 4	--		
0.06 in (1.5 mm)	PLC 2	--		
0.12 in (3.0 mm)	PLC 2	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification				IEC 60695-11-10, -20
0.015 in (0.38 mm)	V-0	--		
0.03 in (0.8 mm)	V-0	--		
0.06 in (1.5 mm)	V-0	--		
0.12 in (3.0 mm)	V-0	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.030 in (0.75 mm)	1760 (960)	--	°F (°C)	
0.06 in (1.5 mm)	1760 (960)	--	°F (°C)	
0.12 in (3.0 mm)	1760 (960)	--	°F (°C)	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.016 in (0.40 mm)	1430 (775)	--	°F (°C)	
0.030 in (0.75 mm)	1430 (775)	--	°F (°C)	
Oxygen Index	35	--	%	ISO 4589-2

Technical Data Sheet



Schulamid 66 MV 5 FR

Polyamide 66
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	500 to 536 °F	260 to 280 °C
Mold Temperature	140 to 212 °F	60 to 100 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Screw Speed	591 in/min	15 m/min

Injection Notes

Mould surface contacting melt should
be of non-corrosive steel (content of chrome > 12%)

Technical Data Sheet

**Schulamid 66 MV 5 FR**

Polyamide 66
LyondellBasell Industries
Engineering Plastics

Notes

¹ 0.079 in/min (2.0 mm/min)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.