

Technical Data Sheet

**Schulink XL 351-L**

Crosslinked Polyethylene
LyondellBasell Industries
Rotomolding

General

Material Status	• Experimental: Active		
Availability	• North America		
Features	• UV Stabilized		
Uses	• Agricultural Applications • Automotive Under the Hood	• High Temperature Applications • Lawn and Garden Equipment	• Tanks
Appearance	• Colors Available	• Natural Color	
Forms	• Powder		
Processing Method	• Rotational Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity ¹	0.944	0.942 g/cm ³	ASTM D792
Environmental Stress-Cracking Resistance (ESCR)			ASTM D1693
10% Igepal, Compression Molded, F50	1000 hr	1000 hr	
100% Igepal, Compression Molded, F50	1000 hr	1000 hr	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Yield, Rotational Molded)	2750 psi	19.0 MPa	ASTM D638
Tensile Elongation ²			ASTM D638
Break, Rotational Molded	300 %	300 %	
Flexural Modulus - 1% Secant (Rotational Molded)	100000 psi	689 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Impact Strength			ARM
-40°F (-40°C), 0.125 in (3.18 mm), Rotational Molded	60 ft·lb	81 J	
-40°F (-40°C), 0.250 in (6.35 mm), Rotational Molded	> 185 ft·lb	> 251 J	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed, Rotational Molded	144 °F	62.0 °C	
264 psi (1.8 MPa), Unannealed, Rotational Molded	95.2 °F	35.1 °C	

Notes

¹ Compression Molded

² 2.0 in/min (51 mm/min)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Page: 1 of 2
LyondellBasell

www.lyondellbasell.com
Publish Date: 2024-03-14

Technical Data Sheet

**Schulink XL 351-L**

Crosslinked Polyethylene
LyondellBasell Industries
Rotomolding

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.