

[Home](#) / [Products & Technology](#) / [Polymers](#) / **Sequel 1440 FP GREY AU**

Sequel 1440 FP GREY AU

Description

Sequel 1440 FP GREY AU engineered polyolefin material is typically used for large automotive exterior applications that require ductile impact properties at low temperatures, excellent paintability, and processability.

Availability

North America

[» CustomerXpress](#)[» Find a Sales Contact](#)[» Request Product Information](#)

Legend

SDS - Safety Data Sheet

PSB - Product Stewardship Bulletin

[Information](#)[SDS](#)[Safety Summary](#)

Product Data and Technical Information

Typical Properties

Melt Flow Rate (230°C/2.16 kg)	22 g/10 min
Density (23°C)	0.94 g/cm ³
Flexural Modulus (23°C, 2mm/min)	1400 MPa
Tensile Stress at Yield (23°C, 50 mm/min)	22 MPa
Notched Izod Impact Strength (23°C)	28 kJ/m ²
Mold Shrinkage	

Process

Injection Molding

Resin

Polypropylene Compounds

Applications

Automotive Parts, Bumpers, Exterior Automotive Applications

Prohibited Applications of Compounded Polyolefins:

The use of LyondellBasell Compounded Polyolefins in the following applications is prohibited:

- All parts for Aeronautical use
- All parts for Train transportation use
- Air bag unit housings
- Seat belt systems and mechanisms
- Brake systems and mechanisms
- Pedals (brake, gas, clutch)
- Steering systems and mechanisms
- All parts with flammability requirements for Building and Constructions
- All parts with flammability requirements for Industrial applications use
- All parts for Medical applications use

This site uses cookies. By continuing to browse the site, you agree to our use of cookies.

[» ACCEPT](#)[Privacy](#)