

[Home](#) / [Products & Technology](#) / [Polymers](#) / **Sequel 1440-UV YGYA EA**

Sequel 1440-UV YGYA EA

Description

Sequel 1440-UV YGYA EA engineered polyolefin material is typically used for large automotive exterior applications that require ductile impact properties at low temperatures, excellent part appearance, and processability.

Availability

North America

[» CustomerXpress](#)[» Find a Sales Contact](#)[» Request Product Information](#)

Legend

SDS - Safety Data Sheet

PSB - Product Stewardship Bulletin

[Information](#)[SDS](#)[Safety Summary](#)

Product Data and Technical Information

Typical Properties

Melt Flow Rate (230°C/2.16 kg)	26 g/10 min
Density (23°C)	0.96 g/cm ³
Tensile Stress at Yield	17 MPa
Tensile Strain at Break	>500 %
Notched Charpy Impact Strength (23°C)	26.9 kJ/m ²
Notched Charpy Impact Strength (-20°C)	9.4 kJ/m ²
Notched Izod Impact Strength (23°C)	24.9 kJ/m ²
Notched Izod Impact Strength (-20°C)	10.0 kJ/m ²
Mold Shrinkage	

Process

Injection Molding

Resin

Polypropylene Compounds

Applications

Automotive Parts, Bumpers, Exterior Automotive Applications

Prohibited Applications of Compounded Polyolefins:

The use of LyondellBasell Compounded Polyolefins in the following applications is prohibited:

- All parts for Aeronautical use
- All parts for Train transportation use
- Air bag unit housings
- Seat belt systems and mechanisms
- Brake systems and mechanisms
- Pedals (brake, gas, clutch)
- Steering systems and mechanisms
- All parts with flammability requirements for Building and Constructions
- All parts with flammability requirements for Industrial applications use
- All parts for Medical applications use

This site uses cookies. By continuing to browse the site, you agree to our use of cookies.

» ACCEPT

[Privacy](#)