



Sequel 1828

Compounded Polyolefin

Product Description

Sequel 1828 thermoplastic polyolefin is designed for automotive and heavy-truck applications that require energy management combined with excellent ductility and stiffness over a broad temperature range. This material exhibits excellent processability and dimensional stability

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	North America
Processing Method	Injection Moulding
Features	Good Dimensional Stability, Ductile, Good Processability, High Stiffness
Typical Customer Applications	Exterior Applications, Bumpers

Typical Properties	Method	Value Unit
Physical		
Density	ISO 1183	1.16 g/cm ³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	12 g/10 min
Mechanical		
Tensile Stress at Yield (50 mm/min)	ISO 527-1, -2	20.0 MPa
<i>Note: 150x10x4 mm specimen</i>		
Flexural modulus (2 mm/min)	ISO 178	2850 MPa
<i>Note: 80x10x4mm specimen</i>		
Impact		
Multiaxial Impact Strength (23 °C, 2.2 m/s)	ASTM D3763	16 J
Additional Information		
Mold shrinkage	ISO 294-4	
<i>Note: Please contact LyondellBasell for shrinkage recommendations.</i>		

Notes

Typical properties; not to be construed as specifications.

Copyright 2009 Basell Service Company B.V. All rights reserved.

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under LyondellBasell's or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of LyondellBasell except in a writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, incidental, punitive or exemplary damages.

CRP, Adflex, Adstif, Adsyl, Akoalit, Akoafloor, Avant, Catalloy, Clyrell, Dexflex, Entegrit, Get in touch with, Hifax, Higran, Histif, Hostacom, Hostalen, Indure, Koattro, LIPP, Lucalen, Luflexen, Lupocomp, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Moplen, Pristene, Purell, Pro-fax, Sequel, Sholybox, Softell, Spherilene, Spheripol, Spherizone, Stretchene, Toppyl and Valtec are trademarks owned or used by LyondellBasell group companies.

Adflex, Adstif, Adsyl, Akoalit, Akoafloor, Avant, Clyrell, CRP, Dexflex, Hifax, Hostacom, Hostalen, Indure, Koattro, Lucalen, Moplen, Purell, Pro-fax, Sequel, Softell, Spheripol, Spherizone and Toppyl are registered in the U.S. Patent and Trademark Office.

Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.

Release Date: 03 Feb 2009