

Technical Data Sheet



Softflex 0954

Thermoplastic Elastomer
LyondellBasell Industries
Engineering Plastics


General			
Material Status	• Commercial: Active		
Availability	• North America		
Forms	• Pellets		
Processing Method	• Coating • Injection Molding		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.09	1.09 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹			ASTM D1238
200°C/5.0 kg	21 g/10 min	21 g/10 min	
235°C/1.0 kg	19 g/10 min	19 g/10 min	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Taber Abrasion Resistance			ASTM D3389
1000 Cycles, 1000 g, H-22 Wheel	238 mg	238 mg	
Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Set (100% Strain)	7 %	7 %	ASTM D412
Tensile Stress			ASTM D412
50% Strain	373 psi	2.57 MPa	
100% Strain	474 psi	3.27 MPa	
300% Strain	711 psi	4.90 MPa	
Tensile Strength ² (Yield)	1380 psi	9.54 MPa	ASTM D412
Tensile Elongation (Break)	810 %	810 %	ASTM D412
Tear Strength	260 lbf/in	45.5 kN/m	ASTM D624
Compression Set ³			ASTM D395B
73°F (23°C), 22 hr	24 %	24 %	
158°F (70°C), 22 hr	78 %	78 %	
212°F (100°C), 22 hr	96 %	96 %	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Gardner Impact (-22°F (-30°C))	> 320 in-lb	> 36.2 J	ASTM D5420
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness			ASTM D2240
Shore A	68 to 78	68 to 78	
Shore A, 10 sec	64 to 74	64 to 74	
Additional Information	Nominal Value (English)	Nominal Value (SI)	
Overmold Bonding	ABS, PC, ABS/PC, PPO	ABS, PC, ABS/PC, PPO	

Technical Data Sheet



Softflex 0954

Thermoplastic Elastomer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	130 to 140 °F	54 to 60 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Suggested Shot Size	40 to 80 %	40 to 80 %
Rear Temperature	320 to 360 °F	160 to 182 °C
Middle Temperature	340 to 380 °F	171 to 193 °C
Front Temperature	410 to 430 °F	210 to 221 °C
Nozzle Temperature	390 to 420 °F	199 to 216 °C
Processing (Melt) Temp	380 to 410 °F	193 to 210 °C
Mold Temperature	80 to 120 °F	27 to 49 °C
Injection Pressure	5000 to 6000 psi	34.5 to 41.4 MPa
Holding Pressure	4000 to 4500 psi	27.6 to 31.0 MPa
Back Pressure	75.0 to 150 psi	0.517 to 1.03 MPa
Screw Speed	20 to 40 rpm	20 to 40 rpm

Technical Data Sheet



Softflex 0954

Thermoplastic Elastomer
LyondellBasell Industries
Engineering Plastics

Notes

¹ Procedure A

² 20 in/min (510 mm/min)

³ 25% Deflection

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.