

Technical Data Sheet

**Softflex 8910**

Thermoplastic Elastomer
LyondellBasell Industries
Engineering Plastics

General

Material Status	• Commercial: Active
Availability	• North America
Uses	• Overmolding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Melt Mass-Flow Rate (MFR) ¹ (224°C/1.2 kg)	25 g/10 min	25 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Taber Abrasion Resistance 3000 Cycles, 1000 g, H-22 Wheel	165 mg	165 mg	ASTM D3389
Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress			ASTM D412
50% Strain	430 psi	2.96 MPa	
100% Strain	680 psi	4.69 MPa	
300% Strain	400 psi	2.76 MPa	
Tensile Strength ² (Yield)	5000 psi	34.5 MPa	ASTM D412
Tensile Elongation (Break)	540 %	540 %	ASTM D412
Tear Strength	500 lbf/in	87.6 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	28 %	28 %	ASTM D395B
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore A)	77	77	ASTM D2240
Additional Information	Nominal Value (English)	Nominal Value (SI)	
Overmold Bonding	ABS, PC, ABS/PC, PPO	ABS, PC, ABS/PC, PPO	

Notes

¹ Procedure A

² 20 in/min (510 mm/min)

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2024

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Technical Data Sheet**Softflex 8910**

Thermoplastic Elastomer
LyondellBasell Industries
Engineering Plastics

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.