



SUPOL HP908E

Compounded Polyolefin

Product Description

SUPOL HP908E is an unfilled UV resistant polypropylene copolymer compound for injection moulding. Designed for automotive applications it is available in custom colours.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Features	Copolymer, Low Density, High Flow , Good Impact Resistance , Medium Rigidity
Typical Customer Applications	Interior Applications

Typical Properties	Method	Value Unit
Physical		
Density	ISO 1183	0.90 g/cm ³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	13 g/10 min
Mechanical		
Flexural modulus	ISO 178	1200 MPa
Impact		
Notched izod impact strength (23, Type 1, Notch A)	ISO 180	20 kJ/m ²

Notes

Typical properties; not to be construed as specifications.

Further Information

SUPOL is a registered trademark of Hyundai Engineering Plastics, Korea Ltd.

SUPOL materials are produced under licence of Hyundai Engineering Plastics, Korea Ltd.

© LyondellBasell Industries Holdings, B.V. 2010

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product(s) may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application.

Users should review the applicable Material Safety Data Sheet before handling the product.

Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Aquamarine, Aquathene, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Duotreat, Filmex, Flexathene, Get in touch with, Glacido, Glidox, Glidsol, Hifax, Histif, Hostacom, Hostalen PP, Hostalen ACP, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupocomp, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Navacet, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-Fax, Punctilious, Purell, SAA 100, SAA 101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, Tetralol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido, Valtec, and Winsense are trademarks owned and/or used by LyondellBasell group companies.

Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Filmex, Flexathene, Glidox, Glidsol, Hifax, Hostacom, Hostalen, Ideal, Indure, Integrate, Koattro, Lucalen, Lupolen, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-Fax, Punctilious, Purell, Sequel, Spheripol, Spherizone, Softell, Starflex, Tebol, Tetralol, T-Hydro, Toppyl, Tufflo, Ultrathene, and Winsense are registered in the U.S. Patent and Trademark Office.

Release Date: 04 Feb 2011