

Ultrathene

UE650028

Preliminary Data Sheet

Ethylene Vinyl Acetate Copolymer

Equivalent Melt Index 3.0 Vinyl Acetate Content 12%



Applications

Ultrathene UE650028 is an EVA copolymer with excellent flexibility and low temperature properties.

Regulatory Status

UE650028 meets the requirements of the Food and Drug Administration regulations 21 CFR 177.1350 and 21 CFR 175.105. These regulations (respectively) allow for the use of this material as articles or components of articles which are "...intended for use in producing, manufacturing, packing, processing, preparing, treating, packaging, transporting or holding food..." and as an adhesive which "...may be safely used as components of articles intended for use in packaging, transporting or holding food." Specific limitations or conditions of use may apply. Please contact your Equistar sales representative for more information regarding the suitability of specific products for specific applications.

Processing Techniques

The maximum recommended melt temperature for UE650028 is 430°F (221°C). Specific recommendations for processing UE650028 can be made only when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.

Typical Properties

Property	Nominal Value	Units	ASTM Test
Equivalent Melt Index ¹	3.0	g/10 min	D 1238
Vinyl Acetate Content	12	%	
DSC Melting Point	91	°C	D 1505
Vicat Softening Point	69	°C	D 1525

¹ The melt index figures are equivalent values correlated from the Melt Flow Rates obtained with ASTM D 1238.

Equistar Chemicals, LP, is a member of the LyondellBasell group companies.

Ultrathene is a trademark owned or used by LyondellBasell group companies. Trademark *Ultrathene* is registered in the U.S. Patent and Trademark Office.

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

Equistar Chemicals, LP
1221 McKinney, Suite 700
P. O. Box 2583
Houston, Texas 77252-2583
(800) 615-8999
www.lyondellbasell.com

3448/0710