


MITSUI CHEMICALS, INC.
<http://www.mitsuichem.com>

Shiodome City Center 1-5-2, Higashi-Shimbashi, Minato-ku, Tokyo 105-7117, Japan

AURUM® PL450C

- FEATURES

Non Reinforced/Filled

Excellent Cleanness (Low Outgassing, Low Level Impurities)

- TYPICAL PROPERTIES

ITEM	TEST METHOD	UNIT	VALUE	
Physical Properties				
S.G.	ASTM D 792	—	1.33	
Mold Shrinkage (MD/TD)	MCI 法	%	0.74/0.85	
Mechanical Properties				
Tensile Strength	ASTM D 638	MPa	92	
Tensile Elongation	ASTM D 638	%	90	
Flexural Strength	ASTM D 790	MPa	137	
Flexural Modulus	ASTM D 790	GPa	2.9	
IZOD Impact Strength	ASTM D 256	J/m	88	
Thermal Properties				
H.D.T. @ 1.82MPa	ASTM D 648	°C	230	
C.L.T.E. (MD/TD)	ASTM D 696	10 ⁻⁵ /K	5.5/5.5	

2010.08.12