

Physical Properties of MLL411

Item	Unit	MLL411
Melting Point	°C	223
MFR	g/10min	22
Tensile Modulus	MPa	410
Yield Stress	MPa	17
Elongation at Break	%	30
Flexural Modulus	MPa	330
Flexural Strength	MPa	13
Izod Impact Strength (with notch)	J/m	-
Vicat Softening Point	°C	134

* The shown TPX data are representative values examined by our standard methods.