

Physical Properties of RT18

**CONFIDENTIAL**

Item	Unit	RT18
Melting Point	°C	232
MFR	g/10min	26
Tensile Modulus	MPa	1900
Yield Stress	MPa	30
Elongation at Break	%	12
Flexural Modulus	MPa	1600
Flexural Strength	MPa	45
Izod Impact Strength (with notch)	J/m	30
Vicat Softening Point	°C	168

* The shown TPX data are representative values examined by our standard methods.