

Physical Properties of RT31

Item	Unit	RT31
Melting Point	°C	232
MFR	g/10min	21
Tensile Modulus	MPa	1900
Yield Stress	MPa	30
Elongation at Break	%	22
Flexural Modulus	MPa	1450
Flexural Strength	MPa	36
Izod Impact Strength (with notch)	J/m	24
Vicat Softening Point	°C	168

* The shown TPX data are representative values examined by our standard methods.