



Teldene® H25FBF Lyondellbasell licensed Spheripol Process
POLYPROPYLENE HOMOPOLYMER

Technical Data Sheet

Typical Applications

- Suitable for extrusion application
- Production of bulk continuous filaments (BCF), continuous filaments (CF) and staple fiber
- Specially used for carpet and upholstery application

Key Characteristics

- Formulated with Phenol-Free anti-gas fading and UV stabilizing Package.
- Enable to run the processes faster than the guaranteed speeds for the Neumag S⁺ machines.

Resin	Conditions	Method	Value	Unit
Density	23°C	ISO 1183	0.900	g/cm ³
Melt Flow Rate (MFR)	230°C/2.16 kg	ASTM D 1238-13	25	g/10-min
Mechanical				
Flexural Modulus		ISO 178	1550	MPa
Tensile modulus		ISO 527-1,2	1622	MPa
Tensile Stress at Break	50-mm/min	ISO 527	36	MPa
Tensile Strain at Break	50-mm/min	ISO 527	> 50	%
Tensile Strain at Yield	50-mm/min	ISO 527	10	%
Izod Notched	23°C	ISO 180	4.5	kJ/m ²
Thermal				
Heat Deflection Temperature	0.45 MPa Un-annealed	ISO 75B	110	°C
Vicat Softening Temperature	A50 (50°C/h 10N)	ISO 306	155	°C

Technical information

Note: The above are typical data representing the product; not to be construed as analysis certificate or specifications.

DS v1.0

For further details about **NATPET** and its products, please visit the website at www.natpet.com

NATPET® products, marketed under the trade name Teldene®, are intended for the use by those customers and/or any other consumers, who undertake to become responsible to independently establish on their own the appropriateness of the product for its intended use, covering all safety and legally enacted requirements at the location of its projected use and the legal disposal practices thereof. The description of the product as given in this sheet shall under no circumstances be construed as warranty, express or implied including a warranty of merchandise fitness for a particular purpose. On behalf of NATPET, no one is authorized to make any such warranties, or take up on their own to assume such a liability. In case of product related claims, the sole and maximum remedy will be the physical substitution of the product or reimbursement of the purchase value, as per NATPET's options. Further claims based on consequential, secondary, castigatory, or extraordinary damages will in no way entertained by NATPET.
NATPET would like to advise its customers and other users that unless specifically stated the supplied products should not be used for applications in medical and/or pharmaceutical sectors.



Teldene[®] H25FBF

Lyondellbasell licensed Spheripol Process

POLYPROPYLENE HOMOPOLYMER

Technical Data Sheet

Special Features

- Woven application
 - Shows broad processing window while providing excellent mechanical properties
 - Tested on Neumag S⁺ machine and qualified by Neumag in their polymer recommendation list
- Non-Woven application
 - Tested on Reicofil[®] 3

Processing Conditions

Average extruder temperature range may be kept between 220-235 °C.

Food Regulation

This product is defined as a preparation under specific food contact regulation. Detailed information will be provided in a relevant document "Regulatory Compliances Product Declaration" upon request.

Storage and Handling

Polypropylene resin should be stored to prevent a direct exposure to sunlight and heat. The Product estimated shelf life is one year starting from production date, adequate humidity below 80%, and temperature below 40°C. Customers might not fully follow the optimal storage condition, hence the shelf life recommended at customer site is six months only as received. Please refer to "Material Safety Datasheet" (MSDS) for handling and storage information.

Documents

Specific documents MSDS and RCPD are available on request. Please send your request to the following e-mail: pa@natpet.com or visit our website : WWW.natpet.com

POLYPROPYLENE HOMOPOLYMER

DS v1.0

For further details about NATPET and its products, please visit the website at www.natpet.com

NATPET[®] products, marketed under the trade name Teldene[®], are intended for the use by those customers and/or any other consumers, who undertake to become responsible to independently establish on their own the appropriateness of the product for its intended use, covering all safety and legally enacted requirements at the location of its projected use and the legal disposal practices thereof. The description of the product as given in this sheet shall under no circumstances be construed as warranty, express or implied including a warranty of merchandise fitness for a particular purpose. On behalf of NATPET, no one is authorized to make any such warranties, or take up on their own to assume such a liability. In case of product related claims, the sole and maximum remedy will be the physical substitution of the product or reimbursement of the purchase value, as per NATPET's options. Further claims based on consequential, secondary, castigatory, or extraordinary damages will in no way entertained by NATPET.

NATPET would like to advise its customers and other users that unless specifically stated the supplied products should not be used for applications in medical and/or pharmaceutical sectors.