


Product Data Sheet

NOVAPOL® PF-Y818 Series Resin

Butene Copolymer LLDPE Film Resin

Grades

PF-Y818-BPX
 PF-Y818-CPX
 PF-Y818-FX

Additive Packages

Slip (1000 ppm), AB (3150 ppm), PPA
 AB (2500 PPM), PPA
 Process stabilizer only

Applications

Food packaging, garment film, trash bags
 Food packaging, industrial packaging, liners
 Food packaging, industrial packaging, stretch wrap, blend

AB = antiblock, PPA - polymer process aid

Property	ASTM ⁽¹⁾	Typical Values ⁽²⁾ for PF-0118-F	
Melt Index ⁽³⁾	D 1238	0.8 g/10 min	
Density	D 792	0.919 g/cm ³	
		METRIC UNITS	ENGLISH UNITS
Film Properties⁽⁴⁾			
Thickness		25 µm	1.0 mil
Tear Strength	MD D 1922	50 g	
	TD	475 g	
Dart Drop Impact, F ₅₀	D 1709/A	115 g	
Low Friction Puncture ⁽⁵⁾		45 J/mm	10 in-lb/mil
Tensile Strength	MD D 882	47 MPa	6,800 psi
	TD	33 MPa	4,800 psi
Yield Strength	MD D 882	10 MPa	1,500 psi
	TD	11 MPa	1,500 psi
Elongation	MD D 882	500 %	500 %
	TD	810 %	810 %
1% Secant Modulus	MD D 882	175 MPa	25,400 psi
	TD	230 MPa	33,400 psi
Haze	D 1003	7 %	7 %
Gloss @ 45°	D 2457	65	65

(1) Properties designated have been determined using methods which are in accordance with, or substantially in accordance with, the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190°C/2.16 kg.

(4) Film properties are typical of blown film extruded on a 2.5" extruder with 4" die and 100-mil die gap at a blow up ratio of 2.5:1, but are dependent upon operating conditions.

(5) NOVA Chemicals test method.

Melt Index **0.8**
Density **0.919**
Features

- Moderate toughness
- Superior melt-strength for high output film lines
- Blends well with LDPE

Common Additives

- Processing stabilizer



Product Data Sheet



NOVAPOL PF-Y818 Series Resin

Butene Copolymer LLDPE Film Resin

Availability

NOVAPOL PF-Y818 Series polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers, or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

Storage/Handling

NOVAPOL PF-Y818 Series resin should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals Safety Data Sheet (SDS) contains important safety information and should be reviewed before using the product.

Processing Conditions

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

Food Packaging Status

United States: NOVAPOL PF-Y818 Series resin complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 3.2a, and may thus be used in the United States as an article or component of an article intended for use in contact with food, without food-type restrictions, under Conditions of Use A–H (21 CFR 176.170(c) Table 2).

Other Countries: For regulatory compliance information for other countries, please contact your nearest NOVA Chemicals office.

Environmental

NOVA Chemicals polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



is the SPI resin code developed for low density and linear low density polyethylene to identify material type for sorting and recycling purposes.

The NOVA Chemicals logo is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.
NOVAPOL® is a registered trademark of NOVA Brands Ltd.; authorized use/utilisation autorisée.

The above information is provided in good faith. NOVA Chemicals is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, NOVA CHEMICALS MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.

March 30, 2021



403.291.8444 | 800.222.7213 x4170 | info@novachem.com | novachemicals.com