



OxyVinyls® 216S



General Description

Type:	Polyvinyl Chloride Homopolymer
Polymerization Process:	Suspension
Appearance:	White, free flowing powder

Features and Uses:

OxyVinyls®216S is suspension PVC resin designed for rigid applications. Its medium molecular weight provides excellent processing characteristics in both single and multi-screw extruders. Its superior color and low contamination qualities make it perfect for vinyl siding and other weatherable building applications.

Vinyl Siding and Soffit
Windows and Doors
Outdoor Furniture

Rigid Profiles
Gutters and Down-spouts
Window Blinds

Resin Properties	Typical Value	Specification Range	Test Method
Inherent Viscosity (dl/g)	0.900	0.880 – 0.920	OxyVinyls 1386
Relative Viscosity	2.15	2.12 – 2.19	Correlation
K Value	64	64 – 65	Correlation
Volatiles (%)	0.10	0.24 Max.	OxyVinyls 1242
Malvern Particle Size			
% Retained on 40 mesh	0.1	0.5 Max.	OxyVinyls 1505
% Retained on 60 mesh	3.5	6.0 Max.	OxyVinyls 1502
% Retained on 200 mesh	6.5	12.0 Max.	
% Retained on Pan	1.0	3.5 Max.	
Residual Monomer (ppm)	0.1	3.2 Max.	OxyVinyls 1005
Apparent Bulk Density (g/cc)	0.542	0.515 – 0.575	OxyVinyls 1501
ASTM Cell Classification	GP4-16340		ASTM D 1755
CAS Number	9002-86-2		

OxyVinyls, LP

Occidental Tower
5005 LBJ Freeway
Dallas, Texas 75244
877-699-8465

Pasadena Plant
January 2012

Important: The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. No warranty or guarantee, express or implied, is made regarding performance, stability or otherwise. This information is not intended to be all-inclusive as the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. While our technical personnel will be happy to respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any Federal, State, or local laws.