



OxyVinyls® 255



General Description

Type: Polyvinyl Chloride Homopolymer
 Polymerization Process: Suspension
 Appearance: White, free flowing powder

Features and Uses:

Medical and Food Grade Flexible Film and Sheet Low Gels and Contamination
 Medical and Food Grade Tubing and Molded Devices Uniform Plasticizer Absorption
 Automotive Molding and Profile Applications Wire and Cable Insulation

Resin Properties	Typical Value	Specification Range	Test Method
Inherent Viscosity (dl/g)	1.12	1.10 – 1.15	OxyVinyls 1386
Relative Viscosity	2.55	2.51 – 2.61	Correlation
K Value	73	72 – 74	Correlation
Volatiles (%)	0.08	0.30 Max.	OxyVinyls 1242
Malvern Particle Size			
% Retained on 40 mesh	0.0	0.2 Max.	OxyVinyls 1505
% Retained on 60 mesh	0.9	2.0 Max.	OxyVinyls 1502
% Retained on 200 mesh	8.9	12.0 Max.	
% Retained on Pan	0.8	2.0 Max.	
Contamination (#/100gm)	4	15 Max.	OxyVinyls 1504
Residual Monomer (ppm)	0.07	4.0 Max.	OxyVinyls 1005
Powder Mix Time (s)	329	275 – 390	OxyVinyls 488
Gels (5' mill results)	8	15 Max.	OxyVinyls 1503
Apparent Bulk Density (g/cc)	0.461	0.440 – 0.520	OxyVinyls 1501
Flow Time (s)	8	12 Max.	OxyVinyls 1501
Color (CIELab b* -value)	0.95	0.25 – 1.40	OxyVinyls 1500
CAS Number	9002-86-2		

OxyVinyls, LP
 Occidental Tower
 5005 LBJ Freeway
 Dallas, Texas 75244
 877-699-8465

Important: The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. No warranty or guarantee, express or implied, is made regarding performance, stability or otherwise. This information is not intended to be all-inclusive as the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. While our technical personnel will be happy to respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as, and nothing herein shall be construed as a recommendation to infringe any existing patents or to violate any Federal, State, or local laws.