

Technical Data Sheet

PETILEN YY S00356
High Density Polyethylene (HDPE)**Description**

PETILEN YY S00356 is a high density polyethylene resin. The structure of the material is bimodal and it has broad molecular weight distribution. The product's excellent ESCR and impact strength prove an advantage especially in large size blow molding applications.

Applications

Blow molding: large-sized (up to 200L) containers, drums for water and chemicals

Compliance to Regulations

The formulation and production of PETILEN YY S00356 conforms to the compositional requirements of the Commission Regulation (EU) No. 10/2011.

Properties	Typical Values (*)	Units	Test Methods
Resin Properties			
Melt Flow Rate (190°C/2.16 kg)	0.04	g/10 min	ASTM D1238
Density, 23°C ⁽¹⁾	0.953	g/cm ³	ASTM D1505
Melting Point (DSC, 2nd heating)	131	°C	ASTM D3418
Mechanical Properties (**)			
Tensile Strength at Yield	24	MPa	ASTM D638
Tensile Strength at Break	36	MPa	ASTM D638
Elongation at Break	830	%	ASTM D638
Flexural Modulus, 23°C	950	MPa	TS EN ISO 178
Izod Impact Strength, 23°C (notched)	660	J/m	ASTM D256
Hardness (Shore D)	63	-	ASTM D2240
Environmental Stress Crack Resistance (10% Igepal, F50)	>600	h	ASTM D1693
Thermal Properties			
Vicat Softening Point, 10 N	128	°C	ASTM D1525

(1) Measured on specimens, prepared according to ASTM D2839.

(*) These are typical properties only and are not to be construed as specifications. Customers should confirm results by their own tests.

(**) The values given are measured based on compression molded sheet.

Technical Data Sheet

PETILEN YY S00356 **High Density Polyethylene (HDPE)**



Recommended Processing Conditions

Blow molding applications;
Typical barrel temperature: 180 - 200°C
Typical melt temperature: 190 - 210°C

Processing conditions should be optimized for different equipment design.

Health, Safety and Food Contact Regulations

The detailed information of the PETILEN YY S00356 product is given in Material Safety Data Sheet and Food Contact Declaration of the product. Please contact your sales representatives or visit web site for the food contact application compliance (e.g. EU, FDA) and other regulatory documents.

Packing and Storage

The material is packaged in PE bags or in PP Big Bags. The product should be stored in a dry area with an ambient temperature below 50°C. It should be kept away from sunlight, sparks, heat and flame. Inappropriate storage conditions can lead to bad smell, color changes and the deterioration in physical properties. It is advised to process PE resins within 6 months after delivery.

Recycling

The product is not hazardous or toxic and it is suitable for recycling using available recycling methods.

Medical Applications Policy

The product mentioned herein is not tested for use in pharmaceutical/medical applications. It is the responsibility of the final product manufacturer to determine that PETKİM product is suitable for intended use.

Disclaimer

© 2022 PETKİM PETROCHEMICAL HOLDING INC. The user may photocopy, distribute and/or forward this document only if unaltered and complete including its headers, footers and other information. You may not publish this document on a website. PETKİM does not guarantee the typical values. The information in this document relates only to the given product when not in combined or compounded with any other materials. The information in this document is based on data reliable on the date compiled. PETKİM may add, remove and/or update information in this document at any time without noticing the users. PETKİM does not guarantee the merchantability, suitability, fitness for particular purpose, accuracy, reliability or completeness of this information or the products specified. The user is solely responsible for any use of the product at any process. PETKİM disclaims liability for any loss, damage or injury directly or indirectly suffered or incurred as a result or related to anyone using or relying on any information in this document.