

RG 1128 N

Product Data and Technical Information

POLYMER TYPE: POLYPROPYLENE HOMOPOLYMER

GRADE NAME : RG 1128 N

PACKING : PP bags of 25 kgs, 50 bags on a pallet shrunk by PE

APPLICATION : Cast films for packaging and stationary films (high slip and antiblock behaviour water cooled blown films)

PRODUCT FEATURES : Homopolymer with good optical properties and high stiffness

PROCESSING METHOD : Extrusion

Property	Test Method	Unit	Value
MFR (230° C/ 2.16 Kg)	ASTM D1238/L	gr/10min	11
Tensile Modulus of Elasticity (1mm/min)	ASTM D638	MPa	1500
Tensile Strength at Yield (50 mm/min)	ASTM D638	MPa	35
Elongation at Yield(50 mm/min)	ASTM D638	%	9
Tear strength(Longitudinal/Transverse)	DIN 53455	MPa	42/38
Flexural modulus (Longitu./Trans.)	DIN 53121	Mpa	700/670
Vicat Softening Point, 10N	ASTM D1525	°C	154
Ball indentation hardness	ISO 2039-1	MPa	76
HDT (0.46 N/mm ²)	ASTM D648	°C	85
Melting Point , DSC	ASTM D3417	°C	163
Density	ASTM D792	gr/cm ³	0.91

"The information in this publication is submitted without prejudice, and is based on our current knowledge and experience and on a limited number of tests.

In view of the many factors that may affect processing and application, these data do not relieve the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply and legally binding assurance of certain properties or of suitability for a specific purpose of the products made with or on the basis of the information in this publication."



Tel: +98(311)6305851-5 Fax: +98(311)6305856 eMail: info@Regalpetro.com