

RG 1142 K

Product Data and Technical Information

POLYMER TYPE: POLYPROPYLENE HOMOPOLYMER

GRADE NAME : RG 1142 K

PACKING : PP bags of 25 kgs, 50 bags on a pallet shrunk by PE

APPLICATION : Thermoformed packaging parts e.g. High transparency dairy and dessert cups

PRODUCT FEATURES : Homopolymer for high transparency thermoforming applications

PROCESSING METHOD : Extrusion

Property	Test Method	Unit	Value
MFR (230° C/ 2.16 Kg)	ASTM D1238/L	gr/10min	3.2
Tensile Modulus of Elasticity (1mm/min)	ASTM D638	MPa	1600
Tensile Strength at Yield (50 mm/min)	ASTM D638	MPa	37
Elongation at Yield(50 mm/min)	ASTM D638	%	9
Notched Charpy Impact at 23°	ISO 179/ 1eA	KJ/m2	4
Notched Charpy Impact at -30°	ISO 179/ 1eA	KJ/m2	1.5
Vicat Softening Point, 10N	ASTM D1525	°C	154
Ball indentation hardness	ISO 2039-1	MPa	78
HDT (0.46 N/mm2)	ASTM D648	°C	90
Melting Point , DSC	ASTM D3417	°C	163
Density	ASTM D792	gr/cm3	0.91

ation in this publication is submitted without prejudice, and is based on our current knowledge and experience of tests

the many factors that may affect processing and application, these data do not relieve the receiver of this information of carrying out their own tests and experiments; neither do they imply and legally binding assurance of certainty or of suitability for a specific purpose of the products made with or on the basis of the information in this publication



Tel: +98(311)6305851-5 Fax: +98(311)6305856 eMail: info@Regalpetro.com