



24FS040 24FA040

LOW DENSITY POLYETHYLENE FOR GENERAL PURPOSE FILM APPLICATIONS

These are blown film grades and can be extruded with considerable ease. 24FS040 has been blended with necessary additives during manufacture to obtain good surface slip and easy open ability between two layers of the film.

24FS040 - With Slip additive.

24FA040 - Without Slip additive

TYPICAL CHARACTERISTICS*

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE**
Density (23°C)	ASTM D 792	g/cc	0.920
Melt Flow Index (190°C / 2.16 Kg)	ASTM D 1238	g/10 min.	4.0
Tensile Strength at Break (MD/TD)	ASTM D 882	MPa	18/16
Elongation at Break (MD/TD)	ASTM D 882	%	250/400
Dart Impact Strength (F ₅₀)	ASTM D 1709/A	g/mic.	2.0

* Typical characteristics and not to be taken as specifications

** Typical properties measured on 40 µm film made with 1.8 mm die gap & 2.5 BUR.

APPLICATIONS:

High slip grade for shopping bags, general purpose packaging. Non-Slip grade can be used for Lamination and bubble wrap applications.

Regulatory Information

• Meets the requirement stipulated in standard IS: 10146 on "Specification for Polyethylene for safe use in contact with foodstuff, pharmaceutical, and drinking water". It also conforms to the positive list of constituents as prescribed in IS: 10141. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21,177,1520, Olefin polymers

Storage Recommendations

• Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

Reliance Industries Limited, Product Application & Research Center (PARC)

RIL Baroda Complex, P. O. Petrochemicals, Vadodara 391346, Gujarat. Tel.: +91-265-6696000. E-mail: polymer_patsupport@ril.com Website: www.ril.com

The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or other wise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.

Nov 2021