



B56003

HIGH DENSITY POLYETHYLENE BLOW MOULDING GRADE

B56003 is a High Density Polyethylene (HDPE) grade suitable for general purpose extrusion blow moulding applications. Articles blown from this grade exhibit good stiffness. The resin offers good melt strength, ESCR and impact resistance and typically used for packaging of oil, vanaspati, general purpose containers, jerry can, etc.

Typical Characteristics*			
Property	Test Method	Unit	Typical Value**
Density (23°C)	ASTM D1505	g/cc	0.956
MFI (190°C/5 kg)	ASTM D1238	g/10 min	1.5
Tensile Strength at Yield	ASTM D 638	MPa	26
Elongation at Break	ASTM D 638	%	550
Flexural Modulus	ASTM D 790	MPa	900
Hardness	ASTM D 2240	Shore D	69
Vicat Softening Point	ASTM D 1525	°C	128

*Typical Characteristics and not to be taken as specifications

**Mechanical Properties are on Injection Moulded Specimen

Applications

Oil, vanaspati and general purpose containers, jerry cans.

Regulatory Information

- Meets the requirements stipulated in standard IS : 10146 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as prescribed in IS : 10141. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21, 177.1520, Olefin polymers.

Storage Recommendations

- Bags should be stored in dry / closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

Reliance Industries Limited, Product and Application Technology Group.

Swastik Mill Compound, V. N. Purav Marg, Chembur, Mumbai-400 071. Tel.: +91-22-6767 7000. E-mail: polymer_patsupport@ril.com Website: www.ril.com

• The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or other wise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.

Updated as of May, 2007