



F46003

HIGH DENSITY POLYETHYLENE BLOW MOULDING & BLOWN FILM GRADE

F46003 is a High Density Polyethylene grade suitable for general purpose blown film & extrusion blow moulding applications. Articles blown from this grade exhibit moderate to good stiffness. The resin offers good melt strength, ESCR and impact resistance.

TYPICAL CHARACTERISTICS*

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE
Density (23°C)	ASTM D 1505	g/cc	0.946
Melt Flow Index (190°C / 2.16 Kg)	ASTM D 1238	g/10 min.	0.38
Film Properties**			
Tensile Strength at Yield (MD / TD)	ASTM D 882	MPa	29.0/26.0
Ultimate Tensile Strength (MD / TD)	ASTM D 882	MPa	45.0/40.0
Elongation at Break (MD / TD)	ASTM D 882	%	780 /950
Dart Impact Strength, F50 (38 mm dart, 66 cm height)	ASTM D 1709	g/ mic.	1.8
Tear Strength (MD / TD)	ASTM D 1922	g/µm	0.4 /4.5

* Typical characteristics and not to be taken as specifications

** Typical properties measured on 40 µm film made with 0.8 mm die gap & 2.7 BUR

APPLICATIONS:

Used for producing blown film and is recommended for use in carry bags and co-extruded film structures, general purpose blow molded containers.

Regulatory Information

- Meets the requirements stipulated in standard IS: I0146 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to IS 16738:2018 "Positive List of Constituents for Polypropylene, Polyethylene and their Copolymers for its Safe Use in Contact with Foodstuffs and Pharmaceuticals"
- The grade and the additives incorporated in it also comply with the FDA: CFR Title 21,177.1520, Olefin polymers

Storage Recommendations

- Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

Reliance Industries Limited, Product Application & Research Center (PARC)

RIL Baroda Complex, P. O. Petrochemicals, Vadodara 391346, Gujarat. Tel.: +91-265-6696000. E-mail: polymer_patsupport@ril.com Website: www.ril.com

The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or other wise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.

Updated ss on Jan 2022