


TECHNICAL DATA SHEET [TDS]
POM Dinaform
REFERENCE: POMC1S15 UV-8126
PRODUCT DESCRIPTION

POM Copolymer Dinaform, UV stabilized, -

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Physical			
Relative density	g/cm ³	ISO 1183	1.41
Mechanical			
Tensile modulus (1 mm/min)	MPa	ISO 527	2600
Stress at break (50 mm/min)	MPa	ISO 527	54
Strain at break (50 mm/min)	%	ISO 527	6
Flexural modulus (2 mm/min)	MPa	ISO 178	2600
Flexural strength (2 mm/min)	MPa	ISO 178	85
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	5
Charpy unnotched impact strength (23°C)	kJ/m ²	ISO 179/1eU	50
Rheological			
Melt flow index M.F.I. (190°C, 2,16 kg)	g/10 min	ISO 1133	11
Thermal			
Heat deflection temperature HDT (1.80 MPa)	°C	ISO 75-A	82
Flammability classification (1.6mm)	V0-V1-V2-HB	UL 94	HB

UPDATE DATE

nov.-2017

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.





TECHNICAL DATA SHEET [TDS]

POM Dinaform

REFERENCE: POMC1S15 UV-8126

PRODUCT DESCRIPTION

POM Copolymer Dinaform, UV stabilized, -

PROPERTIES	UNITS	METHOD	VALUE D.A.M
Processing			
Melt temperature range	°C	-	190-210
Recommended mould temperature	°C	-	60-80
Drying temperature	°C	-	80
Drying time	h	-	3 - 4

UPDATE DATE

nov.-2017

The data submitted here are, to the best of Grupo Repol's knowledge, representative of the range of properties for the listed products, but should not be used to establish process limits or used as the direct basis of design. Colorants or other additives may alter these properties. The data are given for natural grade unless otherwise specified.

